

Fujipoly Industries Sarcon[®] GR-Hd Gap Filler Pad

Category : Polymer , Thermoset , Silicone

Material Notes:

Sarcon GR-d is a highly conformable, thermally conductive material in areas where space between surfaces is uneven and surface textures vary. GR-Hd has a hardened top surface. Information provided by Fujipoly Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_Fujipoly-Industries-Sarcon-GR-Hd-Gap-Filler-Pad.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.60 g/cc	2.60 g/cc	150°C for 1,000 hrs; JIS-K-6220
	2.60 g/cc	2.60 g/cc	JIS-K-6220; ASTM D-792
	2.60 g/cc	2.60 g/cc	70°C for 1,000 hrs; JIS-K-6220
	2.60 g/cc	2.60 g/cc	60°C for 1,000 hrs with 90% RH; JIS-K-6220

Mechanical Properties	Metric	English	Comments
Hardness, Shore C	20	20	60°C for 1,000 hrs with 90% RH; SRIS0101
	22	22	70°C for 1,000 hrs; SRIS0101
	29	29	150°C for 1,000 hrs; SRIS0101
Hardness, Shore OO	49	49	SRIS0101; ASTM D-2240
Tensile Strength, Yield	0.500 MPa	72.5 psi	JIS-K-6251(#2)/ASTM D-412
	0.600 MPa	87.0 psi	150°C for 1,000 hrs; JIS-K-6251(#2)
	0.600 MPa	87.0 psi	60°C for 1,000 hrs with 90% RH; JIS-K-6251(#2)
	0.600 MPa	87.0 psi	70°C for 1,000 hrs; JIS-K-6251(#2)
Elongation at Yield	50 %	50 %	150°C for 1,000 hrs; JIS-K-6251(#2)
	50 %	50 %	60°C for 1,000 hrs with 90% RH; JIS-K-6251(#2)
	60 %	60 %	70°C for 1,000 hrs; JIS-K-6251(#2)
	80 %	80 %	JIS-K-6251(#2)/ASTM D-412
Tear Strength	1.00 kN/m	5.71 pli	60°C for 1,000 hrs with 90% RH; JIS-K-6252 (Angle)
	1.00 kN/m	5.71 pli	150°C for 1,000 hrs; JIS-K-6252 (Angle)

Mechanical Properties	Metric	English	Comments
	1.00 kN/m	5.71 pli	1,000 hrs; JIS-K-6252 (Angle)
	1.00 kN/m	5.71 pli	JIS-K-6252 (Angle)/ASTM D-624

Thermal Properties	Metric	English	Comments
Thermal Conductivity	1.50 W/m-K	10.4 BTU-in/hr-ft ² - ^o F	JIS-R-2618; ASTM D2326
	1.50 W/m-K	10.4 BTU-in/hr-ft ² - ^o F	60 ^o C for 1,000 hrs with 90% RH; JIS-R-2618
	1.50 W/m-K	10.4 BTU-in/hr-ft ² - ^o F	70 ^o C for 1,000 hrs; JIS-R-2618
Maximum Service Temperature, Air	200 ^o C	392 ^o F	
Minimum Service Temperature, Air	-60.0 ^o C	-76.0 ^o F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	JIS-K-6249/ASTM D257
	1.10e+14 ohm-cm	1.10e+14 ohm-cm	60 ^o C for 1,000 hrs with 90% RH; JIS-K-6249
	1.30e+15 ohm-cm	1.30e+15 ohm-cm	70 ^o C for 1,000 hrs; JIS-K-6249
	2.20e+15 ohm-cm	2.20e+15 ohm-cm	150 ^o C for 1,000 hrs; JIS-K-6249
Dielectric Strength	17.0 kV/mm	432 kV/in	JIS-K-6249; ASTM D-149
	20.0 kV/mm	508 kV/in	60 ^o C for 1,000 hrs with 90% RH; JIS-K-6249
	22.0 kV/mm	559 kV/in	70 ^o C for 1,000 hrs; JIS-K-6249
	22.0 kV/mm	559 kV/in	150 ^o C for 1,000 hrs; JIS-K-6249
Dielectric Breakdown	13000 V	13000 V	Withstand Voltage [V/min]; JIS-K-6249; ASTM D-149

Descriptive Properties	Value	Comments
Color	Dark Grey	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China