

## Fujipoly Industries Sarcon<sup>®</sup> XR-j Gap Filler Pad

Category : Polymer , Thermoset , Silicone

### Material Notes:

Sarcon XR-e and XR-j are highly conformable/thermally conductive gel material (no electricity conductive) in a versatile sheet form that easily fits and adheres to most all shapes and sizes of components, and make reliable and complete physical contact. GR-Hn has a hardened top surface. Information provided by Fujipoly Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Fujipoly-Industries-Sarcon-XR-j-Gap-Filler-Pad.php](http://www.lookpolymers.com/polymer_Fujipoly-Industries-Sarcon-XR-j-Gap-Filler-Pad.php)

Physical Properties	Metric	English	Comments
Specific Gravity	3.20 g/cc	3.20 g/cc	JIS-K-6220; ASTM D-792

Mechanical Properties	Metric	English	Comments
Hardness, Shore OO	64	64	ASTM D-2240
Tensile Strength, Yield	0.200 MPa	29.0 psi	JIS-K-6251(#2)/ASTM D-412
Elongation at Yield	40 %	40 %	JIS-K-6251(#2)/ASTM D-412
Tear Strength	1.00 kN/m	5.71 pli	JIS-K-6252 (Angle)/ASTM D-624

Thermal Properties	Metric	English	Comments
Thermal Conductivity	14.0 W/m-K	97.2 BTU-in/hr-ft <sup>2</sup> - °F	ASTM D 5470
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Volume Resistivity	7.40e+11 ohm-cm	7.40e+11 ohm-cm	JIS-K-6249/ASTM D257
Dielectric Strength	18.0 kV/mm	457 kV/in	JIS-K-6249; ASTM D-149
Dielectric Breakdown	11000 V	11000 V	Withstand Voltage [V/min]; JIS-K-6249; ASTM D-149

Descriptive Properties	Value	Comments
Color	Grey	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215, Fengxian District, Shanghai City, China**