

GRECO ISOTHANE 3085A Polyether TPU Resin

Category : Polymer , Thermoplastic , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyether Grade

Material Notes:

ISOTHANE 3000 Series products are polyether based thermoplastic polyurethanes. They exhibit excellent hydrolytic resistance, fungus resistance, and low temperature performance properties. These products can be injection molded, blow molded, and extruded. Information provided by Greater Eastern Resins Industrial Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_GRECO-ISOTHANE-3085A-PolyetherTPUResin.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.13 g/cc	1.13 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	85	85	ASTM D2240
Hardness, Shore D	57	57	ASTM D2240
Tensile Strength	37.0 MPa	5370 psi	ASTM D412
Tensile Strength, Yield	4.50 MPa @Strain 50.0 %	653 psi @Strain 50.0 %	ASTM D412
	5.90 MPa @Strain 100 %	856 psi @Strain 100 %	ASTM D412
	12.0 MPa @Strain 300 %	1740 psi @Strain 300 %	ASTM D412
Elongation at Break	600 %	600 %	ASTM D412
Tear Strength	600 kN/m	3420 pli	ASTM D624
Taber Abrasion, mg/1000 Cycles	20	20	ASTM D1044(Taber) H-22
Compression Set	30 % @Temperature 23.0 Â°C, Time 79200 sec	30 % @Temperature 73.4 Â°F, Time 22.0 hour	ASTM D395
	35 % @Temperature 70.0 Â°C, Time 79200 sec	35 % @Temperature 158 Â°F, Time 22.0 hour	ASTM D395

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China