

GRECO ISOTHANE 3090AF Polyether TPU Resin

Category : Polymer , Thermoplastic , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyether Grade

Material Notes:

ISOTHANE 3000F Series products are polyether based thermoplastic polyurethanes. They exhibit excellent hydrolytic resistance, fungus resistance, and low temperature performance properties. These products can be injection molded, blow molded, and extruded. In compliance with FDA CFR 177.105, 177.1680, and 177.2600 Information provided by Greater Eastern Resins Industrial Co., Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_GRECO-ISOTHANE-3090AF-PolyetherTPUResin.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc	1.14 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	90	90	ASTM D2240
Tensile Strength	41.0 MPa	5950 psi	ASTM D412
Tensile Strength, Yield	6.20 MPa	899 psi	ASTM D412
	@Strain 50.0 %	@Strain 50.0 %	
	8.30 MPa	1200 psi	ASTM D412
	@Strain 100 %	@Strain 100 %	
	17.0 MPa	2470 psi	ASTM D412
	@Strain 300 %	@Strain 300 %	
Elongation at Break	550 %	550 %	ASTM D412
Tear Strength	700 kN/m	3990 pli	ASTM D624
Taber Abrasion, mg/1000 Cycles	50	50	ASTM D1044(Taber) H-22
Compression Set	25 %	25 %	ASTM D395
	@Temperature 23.0 Â°C, Time 79200 sec	@Temperature 73.4 Â°F, Time 22.0 hour	
	40 %	40 %	ASTM D395
	@Temperature 70.0 Â°C, Time 79200 sec	@Temperature 158 Â°F, Time 22.0 hour	

Contact Songhan Plastic Technology Co.,Ltd.Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China