

## GRECO ISOTHANE 5075A Polyether TPU Resin

Category : Polymer , Thermoplastic , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyether Grade

**Material Notes:**

ISOTHANE 5000 Series products are polyether based thermoplastic polyurethanes. They exhibit excellent bio-compatibility, hydrolytic resistance, fungus resistance, and low temperature performance properties. These products can be injection molded, blow molded, and extruded. These are used for biomedical and drug administration applications. Information provided by Greater Eastern Resins Industrial Co., Ltd.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_GRECO-ISOTHANE-5075A-PolyetherTPUResin.php](http://www.lookpolymers.com/polymer_GRECO-ISOTHANE-5075A-PolyetherTPUResin.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	75	75	ASTM D2240
Tensile Strength	31.0 MPa	4500 psi	ASTM D412
Tensile Strength, Yield	2.30 MPa @Strain 50.0 %	334 psi @Strain 50.0 %	ASTM D412
	3.20 MPa @Strain 100 %	464 psi @Strain 100 %	ASTM D412
	5.90 MPa @Strain 300 %	856 psi @Strain 300 %	ASTM D412
Elongation at Break	650 %	650 %	ASTM D412
Tear Strength	400 kN/m	2280 pli	ASTM D624
Taber Abrasion, mg/1000 Cycles	5.0	5.0	ASTM D1044(Taber) H-22
Compression Set	25 % @Temperature 23.0 °C, Time 79200 sec	25 % @Temperature 73.4 °F, Time 22.0 hour	ASTM D395
	35 % @Temperature 70.0 °C, Time 79200 sec	35 % @Temperature 158 °F, Time 22.0 hour	ASTM D395

**Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**