

## Garlock 2930 Compressed Aramid Fiber Gasketing, Neoprene Binder

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

**Material Notes:**

Aramid fibers with a Neoprene binder. Ideal for utility services. Excellent sealability. Improved thermal stability. Good for general service. Media: Water, steam, refrigerants, oils, fuels, mild acids, and mild alkalies. Information provided by Garlock Rubber Technologies

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Garlock-2930-Compressed-Aramid-Fiber-Gasketing-Neoprene-Binder.php](http://www.lookpolymers.com/polymer_Garlock-2930-Compressed-Aramid-Fiber-Gasketing-Neoprene-Binder.php)

Physical Properties	Metric	English	Comments
Density	1.68 g/cc	0.0608 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Tensile Strength	13.8 MPa	2000 psi	across grain; ASTM F152

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	371 Â°C	700 Â°F	
	204 Â°C	400 Â°F	Continuous
	@Pressure 6.89 MPa	@Pressure 1000 psi	
Minimum Service Temperature, Air	-73.3 Â°C	-100 Â°F	

Descriptive Properties	Value	Comments
Color	Black	
Compressibility, %	7-17	ASTM F36
Creep Relaxation, %	22.5	ASTM F38
Sealability ASTM F37B, ml/hr	1	ASTM Fuel A
	2	Nitrogen

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China