

Garlock 8316 EPDM Sheet Rubber Gasketing

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Ethylene propylene diene monomer (EPDM)FDA-approved. Recommended for service against aqueous foods.Information provided by Garlock Rubber Technologies

Order this product through the following link:

http://www.lookpolymers.com/polymer_Garlock-8316-EPDM-Sheet-Rubber-Gasketing.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	55 - 65	55 - 65	ASTM D 2240
Tensile Strength	6.89 MPa	1000 psi	ASTM F152
Elongation at Break	>= 300 %	>= 300 %	ASTM D 395
Compression Set	<= 25 % @Temperature 70.0 Â°C, Time 79200 sec	<= 25 % @Temperature 158 Â°F, Time 22.0 hour	ASTM D 395

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	149 Â°C	300 Â°F	
Minimum Service Temperature, Air	-40.0 Â°C	-40.0 Â°F	

Compliance Properties	Metric	English	Comments
FDA	Yes	Yes	

Descriptive Properties	Value	Comments
Color	Black	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China