

Gharda Chemicals GAFONE™ 3430GF PES, Glass Fiber-Reinforced (discontinued **)

Category : Polymer , Thermoplastic , Polyethersulfone (PES) , Polyethersulfone (PES), 30%Glass Fiber Filled

Material Notes:

Glass fiber reinforced granules for injection molding. With lower viscosity for molding intricate cross sections. Characteristics: Very high rigidity Good dielectric properties High mechanical strength Good dimensional stability Good resistance to hydrolysis and sterilization Good oxidative stability Inherent flame retardance Applications: Reusable hypodermic syringes Surgical instruments and components Printed circuit boards Circuit breaker components Oil level indicators Heat exchanger parts Engine components Household appliances Filter housings Sanitary and pipe fittings Information provided by Gharda. Solvay Advanced Polymers completed its acquisition of this product line in May 2006.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Gharda-Chemicals-GAFONE-3430GF-PES-Glass-Fiber-Reinforced-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.58 g/cc	0.0571 lb/in ³	ISO 1183
Filler Content	30 %	30 %	
Moisture Absorption at Equilibrium	0.25 %	0.25 %	ISO 62
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	120 MPa	17400 psi	After 7 days in boiling water
	140 MPa	20300 psi	ISO 527
Elongation at Break	2.0 %	2.0 %	ISO 527
Tensile Modulus	10.0 GPa	1450 ksi	ISO 527
	10.9 GPa	1580 ksi	After 7 days in boiling water
Flexural Strength	200 MPa	29000 psi	ISO 178
Flexural Modulus	9.00 GPa	1310 ksi	ISO 178
Izod Impact, Notched (ISO)	7.00 kJ/m ²	3.33 ft-lb/in ²	ISO 180/1A

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	185 °C	365 °F	Continuous use
Deflection Temperature at 1.8 MPa (264 psi)	215 °C	419 °F	ISO 75

Glass Transition Temp, Tg Thermal Properties	225 °C Metric	437 °F English	DSC Comments
Flammability, UL94	V-0	V-0	
Oxygen Index	42 %	42 %	ISO 4589

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+16 ohm-cm	>= 1.00e+16 ohm-cm	IEC 93
Surface Resistance	>= 1.00e+14 ohm	>= 1.00e+14 ohm	IEC 93
Dielectric Strength	20.0 kV/mm	508 kV/in	IEC 243/1
Arc Resistance	120 sec	120 sec	ASTM D495
Comparative Tracking Index	150 V	150 V	IEC 112

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China