

## Gharda Chemicals GATONE™ 5300 PEEK, High Viscosity Grade (discontinued \*\*)

Category : Polymer , Thermoplastic , Polyketone , Polyetheretherketone (PEEK) , Polyetheretherketone, PEEK, Unreinforced

### Material Notes:

High viscosity grade for extrusion and injection molding CHARACTERISTICS: Outstanding chemical resistance. Outstanding wear resistance. Outstanding resistance to hydrolysis. Excellent mechanical properties. Outstanding thermal properties. Very good dielectric strength, volume resistivity, tracking resistance. Very good radiation resistance. Information provided by Gharda. Solvay Advanced Polymers completed its acquisition of this product line in May 2006.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Gharda-Chemicals-GATONE-5300-PEEK-High-Viscosity-Grade-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Gharda-Chemicals-GATONE-5300-PEEK-High-Viscosity-Grade-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.32 g/cc	0.0477 lb/in <sup>3</sup>	ISO 118
Moisture Absorption at Equilibrium	0.50 %	0.50 %	ISO 62
Melt Flow	3.96 - 13.2 g/10 min @Load 2.16 kg, Temperature 400 °C	3.96 - 13.2 g/10 min @Load 4.76 lb, Temperature 752 °F	ASTM D1183

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	95.0 MPa	13800 psi	ISO 527
Elongation at Break	45 %	45 %	ISO 527
Tensile Modulus	3.80 GPa	551 ksi	ISO 527
Flexural Strength	150 MPa	21800 psi	ISO 178
Flexural Modulus	4.00 GPa	580 ksi	ISO 178
Izod Impact, Notched	0.600 J/cm	1.12 ft-lb/in	ISO 179

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	260 °C	500 °F	(Expected) Continuous use, UL
Deflection Temperature at 1.8 MPa (264 psi)	150 °C	302 °F	ISO 75
Glass Transition Temp, Tg	148 °C	298 °F	DSC
Flammability, UL94	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00 \times 10^{16}$ ohm-cm	$\geq 1.00 \times 10^{16}$ ohm-cm	IEC 93
Surface Resistance	$\geq 1.00 \times 10^{14}$ ohm	$\geq 1.00 \times 10^{14}$ ohm	IEC 93
Dielectric Strength	19.0 kV/mm	483 kV/in	IEC 243/1

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China