

## Global GPP-240C 40% Glass Reinforced, Chemically Coupled Impact Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Glass Fiber Filler

### Material Notes:

Information provided by Global Polymers Corporation.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Global-GPP-240C-40-Glass-Reinforced-Chemically-Coupled-Impact-Polypropylene.php](http://www.lookpolymers.com/polymer_Global-GPP-240C-40-Glass-Reinforced-Chemically-Coupled-Impact-Polypropylene.php)

Physical Properties	Metric	English	Comments
Density	1.23 g/cc	0.0444 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.0060 cm/cm	0.0060 in/in	ASTM D955
Melt Flow	4.0 g/10 min @Load 2.16 kg, Temperature 230 °C	4.0 g/10 min @Load 4.76 lb, Temperature 446 °F	L; ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	67.6 MPa	9800 psi	ASTM D638
Flexural Modulus	5.10 GPa	740 ksi	ASTM D790
Izod Impact, Notched	1.07 J/cm	2.00 ft-lb/in	ASTM D256

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China