

Global TPP-130 30% Talc Filled Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Talc Filler

Material Notes:

Information provided by Global Polymers Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Global-TPP-130-30-Talc-Filled-Polypropylene.php

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.012 cm/cm	0.012 in/in	ASTM D955
Melt Flow	12 g/10 min @Load 2.16 kg, Temperature 230 °C	12 g/10 min @Load 4.76 lb, Temperature 446 °F	L; ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	31.7 MPa	4600 psi	ASTM D638
Flexural Modulus	3.03 GPa	440 ksi	ASTM D790
Izod Impact, Notched	0.267 J/cm	0.500 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	124 °C	255 °F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China