

## Goodfellow Chromaloy O® Resistance Alloy

Category : Metal , Electronic/Magnetic Alloy , Ferrous Metal , Superalloy , Iron Base

**Material Notes:**

Resistance heating alloy with excellent resistance to oxidation at elevated temperatures. Used in many varied applications - from small household appliances to large industrial furnaces. Information provided by Goodfellow.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Goodfellow-Chromaloy-O-Resistance-Alloy.php](http://www.lookpolymers.com/polymer_Goodfellow-Chromaloy-O-Resistance-Alloy.php)

Physical Properties	Metric	English	Comments
Density	7.10 g/cc	0.257 lb/in <sup>3</sup>	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	650 MPa	94300 psi	
Elongation at Break	15 %	15 %	

Thermal Properties	Metric	English	Comments
CTE, linear	11.0 µm/m-°C @Temperature 20.0 - 100 °C	6.11 µin/in-°F @Temperature 68.0 - 212 °F	
Thermal Conductivity	16.0 W/m-K	111 BTU-in/hr-ft <sup>2</sup> -°F	
Melting Point	1500 °C	2730 °F	
Maximum Service Temperature, Air	1250 °C	2280 °F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	5.0 %	5.0 %	
Chromium, Cr	20 %	20 %	
Iron, Fe	75 %	75 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.000137 ohm-cm	0.000137 ohm-cm	Temperature Coefficient of 0.00007/K
Curie Temperature	600 °C	1110 °F	

**Contact Songhan Plastic Technology Co.,Ltd.**Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China