

Goodfellow Copper 80/Lead 20 Alloy

Category : Metal , Nonferrous Metal , Copper Alloy

Material Notes:

Information provided by Goodfellow.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Goodfellow-Copper-80Lead-20-Alloy.php

Thermal Properties	Metric	English	Comments
Melting Point	1010 °C	1850 °F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	80 %	80 %	
Lead, Pb	20 %	20 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China