

## Goodfellow Iron 50/Nickel 50 Alloy

Category : Metal , Nonferrous Metal , Nickel Alloy

**Material Notes:**

Information provided by Goodfellow.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Goodfellow-Iron-50Nickel-50-Alloy.php](http://www.lookpolymers.com/polymer_Goodfellow-Iron-50Nickel-50-Alloy.php)

Physical Properties	Metric	English	Comments
Density	8.39 g/cc	0.303 lb/in <sup>3</sup>	

Thermal Properties	Metric	English	Comments
Melting Point	1400 - 1450 °C	2550 - 2640 °F	
Solidus	1400 °C	2550 °F	
Liquidus	1450 °C	2640 °F	

Component Elements Properties	Metric	English	Comments
Iron, Fe	50 %	50 %	
Nickel, Ni	50 %	50 %	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China