

Goodfellow Lead 75/Tin 25 Alloy

Category : Metal , Nonferrous Metal , Lead Alloy , Solder/Braze Alloy

Material Notes:

Information provided by Goodfellow.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Goodfellow-Lead-75Tin-25-Alloy.php

| Thermal Properties | Metric | English | Comments |
|--------------------|--------|---------|----------|
| Melting Point | 270 °C | 518 °F | |

| Component Elements Properties | Metric | English | Comments |
|-------------------------------|--------|---------|----------|
| Lead, Pb | 75 % | 75 % | |
| Tin, Sn | 25 % | 25 % | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China