

Goodfellow Magnetic Copper Alloy

Category : Metal , Electronic/Magnetic Alloy , Nonferrous Metal , Copper Alloy

Material Notes:

Information provided by Goodfellow.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Goodfellow-Magnetic-Copper-Alloy.php

Physical Properties	Metric	English	Comments
Density	8.96 g/cc	0.324 lb/in ³	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	539 MPa	78200 psi	
Elongation at Break	1.1 %	1.1 %	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	401 W/m-K	2780 BTU-in/hr-ft ² -°F	

Component Elements Properties	Metric	English	Comments
Copper, Cu	99.96 %	99.96 %	
Iron, Fe	0.040 %	0.040 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China