

Gouda Vuurvast AC 85-5 Dense Refractory Brick

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Description: Excellent resistance against alkali- and metal slags. A good volume stability at very high temperatures. Application: chemical incinerators, combustion chambers for very high temperatures. Remarks: This data represents average values, obtained from samples that were cut from standard bricks. Information provided by Gouda Vuurvast.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Gouda-Vuurvast-AC-85-5-Dense-Refractory-Brick.php

Physical Properties	Metric	English	Comments
Density	3.05 g/cc	0.110 lb/in ³	Apparent
Porosity	16 %	16 %	Apparent

Mechanical Properties	Metric	English	Comments
Compressive Strength	80.0 MPa	11600 psi	Cold Crushing Strength

Thermal Properties	Metric	English	Comments
Thermal Conductivity	2.20 W/m-K	15.3 BTU-in/hr-ft ² - °F	
	@Temperature 1100 °C	@Temperature 2010 °F	
	2.40 W/m-K	16.7 BTU-in/hr-ft ² - °F	
	@Temperature 650 °C	@Temperature 1200 °F	
	2.80 W/m-K	19.4 BTU-in/hr-ft ² - °F	
	@Temperature 100 °C	@Temperature 212 °F	
Maximum Service Temperature, Air	1700 °C	3090 °F	Deformation under load - t _a
	1800 °C	3270 °F	

Component Elements Properties	Metric	English	Comments
Al ₂ O ₃	85 %	85 %	
Cr ₂ O ₃	5.0 %	5.0 %	
Fe ₂ O ₃	0.40 %	0.40 %	

Component Elements Properties	Metric	English	Comments
Descriptive Properties		Value	Comments
Segeccone		42	
Thermal Shock Resistance		20 cycles	DIN 51068

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China