

Gouda Vuurvast AK 50 Dense Refractory Brick

Category : Ceramic , Oxide , Aluminum Oxide , Silicon Oxide

Material Notes:

Description: This brick has a low iron and alkali content and is therefore suitable for use in reducing atmospheres at high temperatures.

Very good resistance to slag attack. Application: incinerators of chemical waste, cement kilns, anode baking furnaces. Remarks: This data represents average values, obtained from samples that were cut from standard bricks. Information provided by Gouda Vuurvast.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Gouda-Vuurvast-AK-50-Dense-Refractory-Brick.php

Physical Properties	Metric	English	Comments
Density	2.35 g/cc	0.0849 lb/in ³	Apparent
Porosity	15 %	15 %	Apparent

Mechanical Properties	Metric	English	Comments
Compressive Strength	50.0 MPa	7250 psi	Cold Crushing Strength

Thermal Properties	Metric	English	Comments
Thermal Conductivity	1.30 W/m-K	9.02 BTU-in/hr-ft ² - °F	
	@Temperature 100 °C	@Temperature 212 °F	
	1.38 W/m-K	9.58 BTU-in/hr-ft ² - °F	
	@Temperature 650 °C	@Temperature 1200 °F	
	1.50 W/m-K	10.4 BTU-in/hr-ft ² - °F	
	@Temperature 1100 °C	@Temperature 2010 °F	
Maximum Service Temperature, Air	1500 °C	2730 °F	
	1540 °C	2800 °F	Deformation under load - t _a

Component Elements Properties	Metric	English	Comments
Al ₂ O ₃	48 %	48 %	
Fe ₂ O ₃	<= 1.2 %	<= 1.2 %	
SiO ₂	47 %	47 %	

Descriptive Properties	Value	Comments
Segecone	35	
Thermal Shock Resistance	15 cycles	DIN 51068

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China