

## Gouda Vuurvast AK 70 M Dense Refractory Brick

Category : Ceramic , Oxide , Aluminum Oxide , Silicon Oxide

### Material Notes:

Description: This mullite brick is characterized by a very good thermal shock resistance, a high resistance against slag penetration and a high strength. Remarks: This data represents average values, obtained from samples that were cut from standard bricks. Information provided by Gouda Vuurvast.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Gouda-Vuurvast-AK-70-M-Dense-Refractory-Brick.php](http://www.lookpolymers.com/polymer_Gouda-Vuurvast-AK-70-M-Dense-Refractory-Brick.php)

Physical Properties	Metric	English	Comments
Density	2.55 g/cc	0.0921 lb/in <sup>3</sup>	Apparent
Porosity	16 %	16 %	Apparent

Mechanical Properties	Metric	English	Comments
Compressive Strength	60.0 MPa	8700 psi	Cold Crushing Strength

Thermal Properties	Metric	English	Comments
Thermal Conductivity	1.90 W/m-K	13.2 BTU-in/hr-ft <sup>2</sup> - °F	
	@Temperature 1100 °C	@Temperature 2010 °F	
	2.00 W/m-K	13.9 BTU-in/hr-ft <sup>2</sup> - °F	
	@Temperature 650 °C	@Temperature 1200 °F	
	2.20 W/m-K	15.3 BTU-in/hr-ft <sup>2</sup> - °F	
	@Temperature 100 °C	@Temperature 212 °F	
Maximum Service Temperature, Air	1700 °C	3090 °F	
	1700 °C	3090 °F	Deformation under load - t <sub>a</sub>

Component Elements Properties	Metric	English	Comments
Al2O3	73 %	73 %	
Fe2O3	<= 0.50 %	<= 0.50 %	
SiO2	25 %	25 %	

Descriptive Properties	Value	Comments
Segecone	40	
Thermal Shock Resistance	30 cycles	DIN 51068

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China