

Gouda Vuurvast AK 85 K Dense Refractory Brick

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Description: Corundum based bricks with a mullite bond. Application: rotating incinerator furnaces
Remarks: This data represents average values, obtained from samples that were cut from standard bricks. Information provided by Gouda Vuurvast.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Gouda-Vuurvast-AK-85-K-Dense-Refractory-Brick.php

Physical Properties	Metric	English	Comments
Density	3.00 g/cc	0.108 lb/in ³	Apparent
Porosity	15 %	15 %	Apparent

Mechanical Properties	Metric	English	Comments
Compressive Strength	80.0 MPa	11600 psi	Cold Crushing Strength

Thermal Properties	Metric	English	Comments
Thermal Conductivity	2.10 W/m-K	14.6 BTU-in/hr-ft ² - °F	
	@Temperature 1100 °C	@Temperature 2010 °F	
	2.30 W/m-K	16.0 BTU-in/hr-ft ² - °F	
	@Temperature 650 °C	@Temperature 1200 °F	
	2.60 W/m-K	18.0 BTU-in/hr-ft ² - °F	
	@Temperature 100 °C	@Temperature 212 °F	
Maximum Service Temperature, Air	>= 1700 °C	>= 3090 °F	Deformation under load - t _a
	1750 °C	3180 °F	

Component Elements Properties	Metric	English	Comments
Al ₂ O ₃	85 %	85 %	
Fe ₂ O ₃	<= 0.50 %	<= 0.50 %	
SiO ₂	13 %	13 %	

Descriptive Properties	Value	Comments
Segecone	39	
Thermal Shock Resistance	30 cycles	DIN 51068

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China