

Gouda Vuurvast B 1 Sp Dense Refractory Brick

Category : Ceramic , Oxide , Aluminum Oxide , Silicon Oxide

Material Notes:

Description: High mechanical strength and very low porosity are typical for this type of brick. Application: transition zone in cement kilns, incinerators, steel ladles. Remarks: This data represents average values, obtained from samples that were cut from standard bricks. Information provided by Gouda Vuurvast.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Gouda-Vuurvast-B-1-Sp-Dense-Refractory-Brick.php

Physical Properties	Metric	English	Comments
Density	2.25 g/cc	0.0813 lb/in ³	Apparent
Porosity	12 %	12 %	Apparent

Mechanical Properties	Metric	English	Comments
Compressive Strength	60.0 MPa	8700 psi	Cold Crushing Strength

Thermal Properties	Metric	English	Comments
Thermal Conductivity	1.12 W/m-K	7.77 BTU-in/hr-ft ² - °F	
	@Temperature 100 °C	@Temperature 212 °F	
	1.25 W/m-K	8.68 BTU-in/hr-ft ² - °F	
	@Temperature 650 °C	@Temperature 1200 °F	
	1.38 W/m-K	9.58 BTU-in/hr-ft ² - °F	
	@Temperature 1100 °C	@Temperature 2010 °F	
Maximum Service Temperature, Air	1350 °C	2460 °F	
	1420 °C	2590 °F	Deformation under load - t _a

Component Elements Properties	Metric	English	Comments
Al ₂ O ₃	39 %	39 %	
Fe ₂ O ₃	<= 2.0 %	<= 2.0 %	
SiO ₂	55 %	55 %	

Descriptive Properties	Value	Comments
Segecone	33	
Thermal Shock Resistance	10 cycles	DIN 51068

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China