

## Gouda Vuurvast C Sp Dense Refractory Brick

Category : Ceramic , Oxide , Aluminum Oxide , Silicon Oxide

### Material Notes:

Description: A fireclay brick for use up to 1200°C. Remarks: This data represents average values, obtained from samples that were cut from standard bricks. Information provided by Gouda Vuurvast.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Gouda-Vuurvast-C-Sp-Dense-Refractory-Brick.php](http://www.lookpolymers.com/polymer_Gouda-Vuurvast-C-Sp-Dense-Refractory-Brick.php)

Physical Properties	Metric	English	Comments
Density	2.10 g/cc	0.0759 lb/in <sup>3</sup>	Apparent
Porosity	15 %	15 %	Apparent

Mechanical Properties	Metric	English	Comments
Compressive Strength	50.0 MPa	7250 psi	Cold Crushing Strength

Thermal Properties	Metric	English	Comments
Thermal Conductivity	0.950 W/m-K	6.59 BTU-in/hr-ft <sup>2</sup> - °F	
	@Temperature 100 °C	@Temperature 212 °F	
	1.10 W/m-K	7.63 BTU-in/hr-ft <sup>2</sup> - °F	
	@Temperature 650 °C	@Temperature 1200 °F	
	1.30 W/m-K	9.02 BTU-in/hr-ft <sup>2</sup> - °F	
	@Temperature 1100 °C	@Temperature 2010 °F	
Maximum Service Temperature, Air	1200 °C	2190 °F	
	1250 °C	2280 °F	Deformation under load - t <sub>a</sub>

Component Elements Properties	Metric	English	Comments
Al <sub>2</sub> O <sub>3</sub>	25 - 28 %	25 - 28 %	
Fe <sub>2</sub> O <sub>3</sub>	2.0 %	2.0 %	
SiO <sub>2</sub>	63 - 66 %	63 - 66 %	

Descriptive Properties	Value	Comments
Segecone	28	
Thermal Shock Resistance	5 cycles	DIN 51068

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China