

Gouda Vuurvast CURAS 90 PF Moldable Refractory Material

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Description: Curas 90 PF ramming mix with outstanding abrasion properties, (erosion loss acc. ASTM C704: 2-4 cm³). The product is supplied in two components: a dry powder and a liquid. Curas 90 PF is applied in the hydrocarbon processing industry. Remarks: The stated chemical composition and physical properties represent average values. Information provided by Gouda Vuurvast.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Gouda-Vuurvast-CURAS-90-PF-Moldable-Refractory-Material.php

Physical Properties	Metric	English	Comments
Bulk Density	2.75 - 2.85 g/cc	0.0994 - 0.103 lb/in ³	After drying at 110 ^o C

Mechanical Properties	Metric	English	Comments
Compressive Strength	85.0 - 95.0 MPa	12300 - 13800 psi	Cold Crushing Strength
	@Temperature 100 ^o C	@Temperature 212 ^o F	
	120 - 140 MPa	17400 - 20300 psi	Cold Crushing Strength
	@Temperature 1600 ^o C	@Temperature 2910 ^o F	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	1.19 - 1.39 W/m-K	8.26 - 9.65 BTU-in/hr-ft ² - ^o F	
	@Temperature 1600 ^o C	@Temperature 2910 ^o F	
	1.23 - 1.43 W/m-K	8.54 - 9.92 BTU-in/hr-ft ² - ^o F	
	@Temperature 600 ^o C	@Temperature 1110 ^o F	
	1.25 - 1.45 W/m-K	8.68 - 10.1 BTU-in/hr-ft ² - ^o F	
	@Temperature 100 ^o C	@Temperature 212 ^o F	
Maximum Service Temperature, Air	1850 ^o C	3360 ^o F	
Shrinkage	-1.10 - 0.900 %	-1.10 - 0.900 %	Permanent Linear Change
	@Temperature 1600 ^o C	@Temperature 2910 ^o F	

Component Elements Properties	Metric	English	Comments
Al ₂ O ₃	90 %	90 %	

Component Elements Properties	Metric	English	Comments
P2O5	3.0 %	3.0 %	
SiO2	6.0 %	6.0 %	

Descriptive Properties	Value	Comments
Bonding Type	chemical/ceramic	
Material Consumption per 1 m3	2850 kg	
Segeccone	40	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China