

Gouda Vuurvast VIBRON 150 Dense Vibrating Refractory Castable

Category : Ceramic , Oxide , Aluminum Oxide

Material Notes:

Description: Vibron 150 is a low cement castable based on sintered bauxite. Remarks: Indicated values apply to vibrated products. Information provided by Gouda Vuurvast.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Gouda-Vuurvast-VIBRON-150-Dense-Vibrating-Refractory-Castable.php

Physical Properties	Metric	English	Comments
Bulk Density	2.80 - 2.90 g/cc	0.101 - 0.105 lb/in ³	After drying at 110 ^o C
Particle Size	<= 7000 μ m	<= 7000 μ m	Grain Size

Mechanical Properties	Metric	English	Comments
Compressive Strength	75.0 - 85.0 MPa	10900 - 12300 psi	Cold Crushing Strength
	@Temperature 100 ^o C	@Temperature 212 ^o F	
Compressive Strength	90.0 - 110 MPa	13100 - 16000 psi	Cold Crushing Strength
	@Temperature 1300 ^o C	@Temperature 2370 ^o F	

Thermal Properties	Metric	English	Comments
Thermal Conductivity	1.77 - 1.97 W/m-K	12.3 - 13.7 BTU-in/hr-ft ² - ^o F	
	@Temperature 100 ^o C	@Temperature 212 ^o F	
Thermal Conductivity	1.77 - 1.97 W/m-K	12.3 - 13.7 BTU-in/hr-ft ² - ^o F	
	@Temperature 600 ^o C	@Temperature 1110 ^o F	
Thermal Conductivity	1.82 - 2.02 W/m-K	12.6 - 14.0 BTU-in/hr-ft ² - ^o F	
	@Temperature 1300 ^o C	@Temperature 2370 ^o F	
Maximum Service Temperature, Air	1500 ^o C	2730 ^o F	
Shrinkage	-0.400 - 0.400 %	-0.400 - 0.400 %	Permanent Linear Change
	@Temperature 1300 ^o C	@Temperature 2370 ^o F	

Component Elements Properties	Metric	English	Comments

Al2O3 Component Elements Properties	82 % Metric	82 % English	Comments
Fe2O3	1.3 %	1.3 %	
SiO2	13 %	13 %	

Descriptive Properties	Value	Comments
Material Consumption per 1 m3	2800 kg	
Mixing Water	5-6 liters	per 100 kgs dry material

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China