

GrafTech eGRAF® HITHERMâ,,¢ HT-2505 Graphite with Polymer Additive

Category: Carbon, Graphite

Material Notes:

Made from natural graphite, eGRAF® HITHERMâ,¢ thermal interface materials are designed for use in applications requiring low contact resistance and high thermal conductivity. HITHERMâ,¢ material is offered in a variety of through thickness thermal conductivities, available in roll or die-cut form and can be laminated with plastics and adhesives. An economical thermal interface material, HITHERMâ,¢ products will not dry out and no outgassing occurs under vacuum conditions. The conformability of HITHERMâ,¢ materials optimizes thermal properties, ensures excellent contact, and is maintained for the life of the assembly. Typical applications include thermal interfaces, chip burn-in, chip testing fixtures, DC-to-DC converters, CPU modules, microprocessors, and hot and cold plates.

Order this product through the following link:

http://www.lookpolymers.com/polymer_GrafTech-eGRAF-HITHERM-HT-2505-Graphite-with-Polymer-Additive.php

Physical Properties	Metric	English	Comments
Thickness	127 microns	5.00 mil	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	1.40 MPa	203 psi	ASTM-F152

Thermal Properties	Metric	English	Comments
CTE, linear	-0.400 Âμm/m-°C	-0.222 Âμin/in-°F	In-Plane
	27.0 Âμm/m-°C	15.0 Âμin/in-°F	Through Thickness
Specific Heat Capacity	0.711 J/g-°C	0.170 BTU/lb-°F	
Thermal Conductivity	16.0 W/m-K	111 BTU-in/hr-ft²-°F	Through Thickness; ASTM-D5470 Modified (at 110kPa/16 psi/1.1 bar)
	120 W/m-K	833 BTU-in/hr-ft²-°F	In-Plane; Angstrom's Method
Maximum Service Temperature, Air	125 °C	257 °F	
Minimum Service Temperature, Air	-25.0 °C	-13.0 °F	
Flammability, UL94	V-0	V-0	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.00100 ohm-cm	0.00100 ohm-cm	In-Plane
	1.50 ohm-cm	1.50 ohm-cm	Through Thickness

Descriptive Properties	Value	Comments



Thermal Contact Impedance - Per Side (A*CA-cmA*/W) Descriptive Properties	Value	et 700 kPa/100 psi/6.9 bar Comments
	0.19	at 100 kPa/14.5 psi/1 bar

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China