

Greene Tweed CHEMRAZ® 629 Perfluoroelastomer

Category: Polymer, Thermoset, Fluoropolymer, TS, Thermoset Fluoroelastomer, Rubber or Thermoset Elastomer (TSE)

Material Notes:

Chemraz® 629 perfluoroelastomer is specifically developed by Greene Tweed to meet the rigorous demands of aggressive plasma systems. This product's unique formulation provides enhanced plasma resistance in oxygen and fluorine plasma processes resulting in minimal contamination, less downtime and higher wafer processing yields. Chemraz 629 is developed from an advanced polymer utilizing fluoro-polymer nano-composite technology particles. Recommended for both static and dynamic dry wafer processing applications such as etch, remote plasma cleans, and deposition (CVD, HDPCVD, etc.) with challenging gland designs and reduced sealing loads. Chemraz 629 remains stable at service temperatures up to 260°C (500°F). Applications: Endpoint windows Bell jar seals Valve seals KF fitting seals Window seals loads to valve seals Lid seals Gas inlet seals Chamber seals Chamber seals Information provided by Greene Tweed.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Greene-Tweed-CHEMRAZ-629-Perfluoroelastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.07 g/cc	2.07 g/cc	ASTM D297

Mechanical Properties	Metric	English	Comments	
Hardness, Shore A	75	75	ASTM D2240	
Tensile Strength at Break	15.34 MPa	2225 psi	ASTM D1414	
Tensile Strength, Yield	2.07 MPa	300 psi	@50% Elongation; ASTM D1414	
	4.21 MPa	610 psi	@100% Elongation; ASTM D1414	
Elongation at Break	215 %	215 %	ASTM D1414	
Compression Set	30 %	30 %	70 hours @ 400°F (204°C) @ 25% deflection; ASTM D395	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	260 °C	500 °F	
Minimum Service Temperature, Air	-20.0 °C	-4.00 °F	

Descriptive Properties	Value	Comments
Color	Translucent Ivory	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com



Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China