

## Gromax BFG45-DN00N1 Nylon 6 46% Glass Filled (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 50% Glass Fiber Filled

### Material Notes:

Information provided by Gromax Enterprises Corp.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Gromax-BFG45-DN00N1-Nylon-6-46-Glass-Filled-Dry.php](http://www.lookpolymers.com/polymer_Gromax-BFG45-DN00N1-Nylon-6-46-Glass-Filled-Dry.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.60 g/cc	1.60 g/cc	ISO 1183
Moisture Absorption	0.800 %	0.800 %	ISO 62
Maximum Moisture Content	0.10	0.10	Karl Fischer
Linear Mold Shrinkage, Flow	0.0020 cm/cm @Temperature 80.0 Â°C	0.0020 in/in @Temperature 176 Â°F	60x60x2 mm; ISO 294-4
Linear Mold Shrinkage, Transverse	0.0060 cm/cm @Temperature 80.0 Â°C	0.0060 in/in @Temperature 176 Â°F	60x60x2 mm; ISO 294-4

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	94	94	[N/mm<sup>2</sup>]; ISO 7619
Tensile Strength	167 MPa	24200 psi	50 mm/min; ISO 527-1,-2
Elongation at Break	2.2 %	2.2 %	50 mm/min; ISO 527
Tensile Modulus	8.80 GPa	1280 ksi	1 mm/min; ISO 527-1,-2
Flexural Strength	250 MPa	36300 psi	5 mm/min; ISO 178
Flexural Modulus	10.4 GPa	1510 ksi	5 mm/min; ISO 178
Izod Impact, Notched (ISO)	13.7 kJ/mÂ²	6.52 ft-lb/inÂ²	ISO 180-1A
Charpy Impact Unnotched	8.60 J/cmÂ² @Temperature 23.0 Â°C	40.9 ft-lb/inÂ² @Temperature 73.4 Â°F	ISO 179-1eU
Charpy Impact, Notched	1.40 J/cmÂ² @Temperature 23.0 Â°C	6.66 ft-lb/inÂ² @Temperature 73.4 Â°F	ISO 179-1A

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Melting Point Thermal Properties	220 Â°C Metric	428 Â°F English	10Â°C/min: ISO 11357-1,-3 Comments
Deflection Temperature at 0.46 MPa (66 psi)	222 Â°C	432 Â°F	ISO 75-1,-2
Deflection Temperature at 1.8 MPa (264 psi)	212 Â°C	414 Â°F	ISO 75-1,-2
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Processing Properties	Metric	English	Comments
Melt Temperature	280 - 300 Â°C	536 - 572 Â°F	ISO 294
Mold Temperature	80.0 - 120 Â°C	176 - 248 Â°F	ISO 294
Drying Temperature	80.0 Â°C	176 Â°F	
Dry Time	2.00 - 6.00 hour	2.00 - 6.00 hour	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China