

Gromax BFM30-EL04B2 Nylon 6 30% Mineral Filled (Conditioned)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Mineral Filled

Material Notes:

Information provided by Gromax Enterprises Corp.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Gromax-BFM30-EL04B2-Nylon-6-30-Mineral-Filled-Conditioned.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.40 g/cc	1.40 g/cc	ISO 1183
Moisture Absorption	0.900 %	0.900 %	ISO 62
Maximum Moisture Content	0.10	0.10	Karl Fischer

Thermal Properties	Metric	English	Comments
Melting Point	220 Â°C	428 Â°F	10Â°C/min; ISO 11357-1,-3
Deflection Temperature at 1.8 MPa (264 psi)	177 Â°C	351 Â°F	ISO 75-1,-2
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Processing Properties	Metric	English	Comments
Melt Temperature	266 - 280 Â°C	511 - 536 Â°F	ISO 294
Mold Temperature	80.0 - 120 Â°C	176 - 248 Â°F	ISO 294
Drying Temperature	80.0 Â°C	176 Â°F	
Dry Time	2.00 - 6.00 hour	2.00 - 6.00 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China