

## Gromax BTE25-DN00N1 Nylon 6 (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

### Material Notes:

Information provided by Gromax Enterprises Corp.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Gromax-BTE25-DN00N1-Nylon-6-Dry.php](http://www.lookpolymers.com/polymer_Gromax-BTE25-DN00N1-Nylon-6-Dry.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.09 g/cc	1.09 g/cc	ISO 1183
Moisture Absorption	1.80 %	1.80 %	ISO 62
Maximum Moisture Content	0.10	0.10	Karl Fischer
Linear Mold Shrinkage, Flow	0.018 cm/cm	0.018 in/in	60x60x2 mm; ISO 294-4
Linear Mold Shrinkage, Transverse	0.019 cm/cm	0.019 in/in	60x60x2 mm; ISO 294-4

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	68	68	[N/mm <sup>2</sup> ]; ISO 7619
Tensile Strength	54.9 MPa	7970 psi	50 mm/min; ISO 527-1,-2
Elongation at Break	85 %	85 %	50 mm/min; ISO 527
Flexural Strength	77.0 MPa	11200 psi	5 mm/min; ISO 178
Flexural Modulus	1.96 GPa	284 ksi	5 mm/min; ISO 178
Izod Impact, Notched	>= NB	>= NB	5 mm/min; ISO 178
Izod Impact, Notched (ISO)	22.0 kJ/m <sup>2</sup>	10.5 ft-lb/in <sup>2</sup>	ISO 180-1A
Charpy Impact Unnotched	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 179-1eU
Charpy Impact, Notched	0.650 J/cm <sup>2</sup> @Temperature -30.0 °C	3.09 ft-lb/in <sup>2</sup> @Temperature -22.0 °F	ISO 179-1A
	2.70 J/cm <sup>2</sup> @Temperature 23.0 °C	12.8 ft-lb/in <sup>2</sup> @Temperature 73.4 °F	ISO 179-1A

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Melting Point Thermal Properties	220 Â°C Metric	428 Â°F English	10Â°C/min: ISO 11357-1,-3 Comments
Deflection Temperature at 1.8 MPa (264 psi)	62.0 Â°C	144 Â°F	ISO 75-1,-2
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Processing Properties	Metric	English	Comments
Melt Temperature	230 - 260 Â°C	446 - 500 Â°F	ISO 294
Mold Temperature	80.0 - 120 Â°C	176 - 248 Â°F	ISO 294
Drying Temperature	80.0 Â°C	176 Â°F	
Dry Time	2.00 - 6.00 hour	2.00 - 6.00 hour	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China