

Gromax BTE30-FN00N1 Nylon 6 (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

Information provided by Gromax Enterprises Corp.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Gromax-BTE30-FN00N1-Nylon-6-Dry.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.09 g/cc	1.09 g/cc	ISO 1183
Moisture Absorption	1.80 %	1.80 %	ISO 62
Maximum Moisture Content	0.10	0.10	Karl Fischer
Linear Mold Shrinkage, Flow	0.018 cm/cm	0.018 in/in	60x60x2 mm; ISO 294-4
Linear Mold Shrinkage, Transverse	0.019 cm/cm	0.019 in/in	60x60x2 mm; ISO 294-4

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	69	69	[N/mm²]; ISO 7619
Tensile Strength	60.8 MPa	8820 psi	50 mm/min; ISO 527-1,-2
Elongation at Break	70 %	70 %	50 mm/min; ISO 527
Flexural Strength	80.0 MPa	11600 psi	5 mm/min; ISO 178
Flexural Modulus	2.06 GPa	299 ksi	5 mm/min; ISO 178
Izod Impact, Notched	>= NB	>= NB	5 mm/min; ISO 178
Izod Impact, Notched (ISO)	30.0 kJ/m ²	14.3 ft-lb/in ²	ISO 180-1A
Charpy Impact Unnotched	NB @Temperature 23.0 °C	NB @Temperature 73.4 °F	ISO 179-1eU
Charpy Impact, Notched	0.880 J/cm ² @Temperature -30.0 °C	4.19 ft-lb/in ² @Temperature -22.0 °F	ISO 179-1A
	3.60 J/cm ² @Temperature 23.0 °C	17.1 ft-lb/in ² @Temperature 73.4 °F	ISO 179-1A

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Melting Point Thermal Properties	220 Â°C Metric	428 Â°F English	10Â°C/min: ISO 11357-1,-3 Comments
Deflection Temperature at 1.8 MPa (264 psi)	63.0 Â°C	145 Â°F	ISO 75-1,-2
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Processing Properties	Metric	English	Comments
Melt Temperature	230 - 260 Â°C	446 - 500 Â°F	ISO 294
Mold Temperature	80.0 - 120 Â°C	176 - 248 Â°F	ISO 294
Drying Temperature	80.0 Â°C	176 Â°F	
Dry Time	2.00 - 6.00 hour	2.00 - 6.00 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China