

Gromax CCP PBT 3030-200HR 30% Glass Fiber Filled

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 30% Glass Fiber Filled

Material Notes:

Product Description: A glass fiber 30% reinforced injection molding grade. Characteristics:Excellent electrical property Excellent temperature resistance, high heat distortion temperature Excellent mechanic and chemical property Excellent weatherability Excellent wear property Excellent moldability High resistance to fuels, oil, fats and many solventsHigh hydrolysis resistanceInformation provided by Gromax Enterprises Corp.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Gromax-CCP-PBT-3030-200HR-30-Glass-Fiber-Filled.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.50 g/cc	1.50 g/cc	ASTM D792
Moisture Absorption	0.0400 % @Time 86400 sec	0.0400 % @Time 24.0 hour	ASTM D570
Linear Mold Shrinkage	0.0020 - 0.0050 cm/cm @Thickness 1.60 mm	0.0020 - 0.0050 in/in @Thickness 0.0630 in	horizontal; ASTM D955
	0.0080 - 0.014 cm/cm @Thickness 1.60 mm	0.0080 - 0.014 in/in @Thickness 0.0630 in	vertical; ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	121	121	ASTM D785
Tensile Strength	127 MPa	18300 psi	ASTM D638
Elongation at Break	4.0 %	4.0 %	ASTM D638
Flexural Strength	202 MPa	29300 psi	ASTM D790
Flexural Modulus	8.04 GPa	1170 ksi	ASTM D790
Izod Impact, Notched	>= 1.16 J/cm @Thickness 6.35 mm	>= 2.17 ft-lb/in @Thickness 0.250 in	ASTM D256

Thermal Properties	Metric	English	Comments
CTE, linear	30.0 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	16.7 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	ASTM D696
Melting Point	225 $^{\circ}\text{C}$	437 $^{\circ}\text{F}$	DSC
Deflection Temperature at 0.46 MPa (66 psi)	220 $^{\circ}\text{C}$	428 $^{\circ}\text{F}$	ASTM D648

Thermal Properties <small>(Deflection Temperature at 1.8 MPa 100 psi)</small>	205 °C Metric	401 °F English	ASTM D649 Comments
Flammability, UL94	HB @Thickness 0.800 mm	HB @Thickness 0.0315 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	ASTM D257
Surface Resistance	1.00e+13 ohm	1.00e+13 ohm	ASTM D257
Dielectric Constant	3.7 @Frequency 60.0 Hz	3.7 @Frequency 60.0 Hz	ASTM D150
Dielectric Strength	24.0 kV/mm @Thickness 2.00 mm	610 kV/in @Thickness 0.0787 in	ASTM D149
Dissipation Factor	0.0010 @Frequency 60.0 Hz	0.0010 @Frequency 60.0 Hz	ASTM D150
Arc Resistance	100 sec	100 sec	ASTM D495

Processing Properties	Metric	English	Comments
Processing Temperature	240 - 270 °C	464 - 518 °F	
Nozzle Temperature	260 - 270 °C	500 - 518 °F	
Mold Temperature	40.0 - 120 °C	104 - 248 °F	suitable temperature 60-80°C
Injection Pressure	50.0 - 120 MPa	7250 - 17400 psi	
Hold Pressure	30.0 - 80.0 MPa	4350 - 11600 psi	
Back Pressure	0.000 - 0.300 MPa	0.000 - 43.5 psi	
Screw Speed	60 - 120 rpm	60 - 120 rpm	to be chosen in such a way that plasticizing time is just within cooling time

Descriptive Properties	Value	Comments
Injection Rate	middle-fast	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China