

Gromax CFG30-SN31N1 Nylon 6 30% Glass Filled (Dry)

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Glass Fiber Filled

Material Notes:

Information provided by Gromax Enterprises Corp.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Gromax-CFG30-SN31N1-Nylon-6-30-Glass-Filled-Dry.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.36 g/cc	1.36 g/cc	ISO 1183
Moisture Absorption	0.900 %	0.900 %	ISO 62
Maximum Moisture Content	0.10	0.10	Karl Fischer
Linear Mold Shrinkage, Flow	0.0030 cm/cm @Temperature 80.0 °C	0.0030 in/in @Temperature 176 °F	60x60x2 mm; ISO 294-4
Linear Mold Shrinkage, Transverse	0.0070 cm/cm @Temperature 80.0 °C	0.0070 in/in @Temperature 176 °F	60x60x2 mm; ISO 294-4

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	82	82	[N/mm ²]; ISO 7619
Tensile Strength	163 MPa	23600 psi	50 mm/min; ISO 527
Elongation at Break	3.4 %	3.4 %	50 mm/min; ISO 527
Flexural Strength	240 MPa	34800 psi	5 mm/min; ISO 178
Flexural Modulus	7.65 GPa	1110 ksi	5 mm/min; ISO 178
Izod Impact, Notched (ISO)	12.6 kJ/m ²	6.00 ft-lb/in ²	ISO 180-1A
Charpy Impact Unnotched	6.00 J/cm ² @Temperature 23.0 °C	28.6 ft-lb/in ² @Temperature 73.4 °F	ISO 179-1eU
Charpy Impact, Notched	1.32 J/cm ² @Temperature 23.0 °C	6.28 ft-lb/in ² @Temperature 73.4 °F	ISO 179-1A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	240 °C	464 °F	ISO 75-1,-2
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Thermal Properties	Metric	English	Comments
Processing Properties	Metric	English	Comments
Melt Temperature	266 - 280 °C	511 - 536 °F	ISO 294
Mold Temperature	80.0 - 120 °C	176 - 248 °F	ISO 294
Drying Temperature	80.0 °C	176 °F	
Dry Time	2.00 - 6.00 hour	2.00 - 6.00 hour	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China