

Guarniflon PTFE G200 Polytetrafluoroethylene

Category : Polymer , Thermoplastic , Fluoropolymer , PTFE , Polytetrafluoroethylene (PTFE), Extruded , Polytetrafluoroethylene (PTFE), Molded

Material Notes:

A virgin PTFE with low coefficient of friction, excellent chemical inertness, non-adhesive surface, wide service temperature range, and excellent dielectric properties. Information provided by Guarniflon®

Order this product through the following link:

http://www.lookpolymers.com/polymer_Guarniflon-PTFE-G200-Polytetrafluoroethylene.php

Physical Properties	Metric	English	Comments
Density	2.13 - 2.20 g/cc	0.0770 - 0.0795 lb/in ³	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength	>= 13.0 MPa	>= 1890 psi	extruded; ASTM D1708
	>= 13.0 MPa	>= 1890 psi	molded; ASTM D1708
Elongation at Break	>= 100 %	>= 100 %	extruded; ASTM D1708
	>= 150 %	>= 150 %	molded; ASTM D1708
Compressive Yield Strength	2.00 - 4.00 MPa	290 - 580 psi	ASTM D695
	@Strain 1.00 %	@Strain 1.00 %	
Coefficient of Friction, Dynamic	0.060	0.060	ASTM D1894

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	260 °C	500 °F	
Minimum Service Temperature, Air	-200 °C	-328 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China