

Gwent Electronic Materials C2030325D14 Curable Carbon Ink

Category: Fluid, Other Engineering Material, Additive/Filler for Polymer

Material Notes:

This product is based on a unique curing process that results in the low temperature formation of a thermosetting conductive coating that combines good adhesion with excellent chemical, solvent and abrasion resistance. It offers the advantage of a One-Pak cure system combined with the convenience of Ambient Temperature stability, which means they do not have to be stored in a freezer or refrigerator. Chemical Resistant GradeInformation provided by Gwent Electronic Materials Ltd.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Gwent-Electronic-Materials-C2030325D14-Curable-Carbon-Ink.php

Physical Properties	Metric	English	Comments
Particle Size	<= 5.0 Âμm	<= 5.0 Âμm	Fineness of Grind
	12000 cP	12000 cP	Haake Viscosity
Viscosity	@Shear Rate 230 1/s, Temperature 25.0 °C	@Shear Rate 230 1/s, Temperature 77.0 °F	
Thickness	20.0 - 30.0 microns	0.787 - 1.18 mil	

Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	<= 100 ohm	<= 100 ohm	cured; 25 microns thick

	Processing Properties	Metric	English	Comments
	Cure Time	30.0 - 60.0 min	0.500 - 1.00 hour	
Cure rime	@Temperature 180 °C	@Temperature 356 °F		

Descriptive Properties	Value	Comments
Coverage cm2/g	190	200 mesh stainless steel screen
Printing Mesh counts/inch	180 to 340	stainless steel or polyester screens

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China