

## H.C. Starck Ampersint® MAP FeCo 50/50 For Soft Magnets

Category : Metal , Electronic/Magnetic Alloy , Nonferrous Metal , Cobalt Alloy

**Material Notes:**

High-temperature, oxidation-resistant, abrasion-resistant and biocompatible materials can be processed with all standard powder metallurgical technologies. The customized alloy can be supplied as a ready-to-process Ampersint® Map powder.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_HC-Starck-Ampersint-MAP-FeCo-5050-For-Soft-Magnets.php](http://www.lookpolymers.com/polymer_HC-Starck-Ampersint-MAP-FeCo-5050-For-Soft-Magnets.php)

Physical Properties	Metric	English	Comments
Density	8.15 g/cc	0.294 lb/in <sup>3</sup>	
Porosity	<= 3 %	<= 3 %	sintered

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	650 MPa	94300 psi	
	@Temperature 600 Â°C	@Temperature 1110 Â°F	
	700 MPa	102000 psi	
	@Temperature 400 Â°C	@Temperature 752 Â°F	
	710 MPa	103000 psi	
	@Temperature 200 Â°C	@Temperature 392 Â°F	

Component Elements Properties	Metric	English	Comments
Carbon, C	1.0 %	1.0 %	
Cobalt, Co	49 - 51 %	49 - 51 %	
Iron, Fe	49 - 51 %	49 - 51 %	

Electrical Properties	Metric	English	Comments
Magnetic Permeability	7577	7577	
Magnetic Coercive Force, Hc	1.696 Oe	1.696 Oe	
Magnetic Saturation Flux Density, Bmax	22000 Gauss	22000 Gauss	

**Contact Songhan Plastic Technology Co.,Ltd.**Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China