

## H.C. Starck Ampersint® MAP FeCoNi 40/20/40 For Hardmetals

Category : Metal

**Material Notes:**

High-temperature, oxidation-resistant, abrasion-resistant and biocompatible materials can be processed with all standard powder metallurgical technologies. The customized alloy can be supplied as a ready-to-process Ampersint® Map powder.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_HC-Starck-Ampersint-MAP-FeCoNi-402040-For-Hardmetals.php](http://www.lookpolymers.com/polymer_HC-Starck-Ampersint-MAP-FeCoNi-402040-For-Hardmetals.php)

Physical Properties	Metric	English	Comments
Particle Size	1.0 - 2.0 $\mu\text{m}$	1.0 - 2.0 $\mu\text{m}$	FSSS

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	650 MPa	94300 psi	
	@Temperature 600 $^{\circ}\text{C}$	@Temperature 1110 $^{\circ}\text{F}$	
	700 MPa	102000 psi	
	@Temperature 400 $^{\circ}\text{C}$	@Temperature 752 $^{\circ}\text{F}$	
	710 MPa	103000 psi	
	@Temperature 200 $^{\circ}\text{C}$	@Temperature 392 $^{\circ}\text{F}$	

Component Elements Properties	Metric	English	Comments
Carbon, C	0.10 %	0.10 %	
Cobalt, Co	19 - 21 %	19 - 21 %	
Iron, Fe	39 - 41 %	39 - 41 %	
Nickel, Ni	39 - 41 %	39 - 41 %	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China