

H.C. Starck Ampersint® MAP FeNi 50/50 For Hardmetals

Category : Metal , Ferrous Metal , Nonferrous Metal , Nickel Alloy

Material Notes:

High-temperature, oxidation-resistant, abrasion-resistant and biocompatible materials can be processed with all standard powder metallurgical technologies. The customized alloy can be supplied as a ready-to-process Ampersint® Map powder.

Order this product through the following link:

http://www.lookpolymers.com/polymer_HC-Starck-Ampersint-MAP-FeNi-5050-For-Hardmetals.php

Physical Properties	Metric	English	Comments
Density	8.25 g/cc	0.298 lb/in ³	
Particle Size	1.0 - 2.0 µm	1.0 - 2.0 µm	FSSS

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	650 MPa	94300 psi	
	@Temperature 600 °C	@Temperature 1110 °F	
	700 MPa	102000 psi	
	@Temperature 400 °C	@Temperature 752 °F	
	710 MPa	103000 psi	
	@Temperature 200 °C	@Temperature 392 °F	

Component Elements Properties	Metric	English	Comments
Carbon, C	0.10 %	0.10 %	
Iron, Fe	49 - 51 %	49 - 51 %	
Nickel, Ni	49 - 51 %	49 - 51 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China