

## H.C. Starck Pure Molybdenum GME Glass Melting Electrodes

Category : Metal , Nonferrous Metal , Molybdenum Alloy , Refractory Metal , Pure Element

### Material Notes:

Glass Melting Electrodes Description of Product: This specification covers Molybdenum Glass Melting Electrodes. Structure: Glass melting electrodes will normally be shipped as stress relieved. Material can also be supplied in the re-crystallized condition. Information provided by H.C. Starck.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_HC-Starck-Pure-Molybdenum-GME-Glass-Melting-Electrodes.php](http://www.lookpolymers.com/polymer_HC-Starck-Pure-Molybdenum-GME-Glass-Melting-Electrodes.php)

Component Elements Properties	Metric	English	Comments
Aluminum, Al	<= 0.0020 %	<= 0.0020 %	
Calcium, Ca	<= 0.0030 %	<= 0.0030 %	
Carbon, C	<= 0.0050 %	<= 0.0050 %	
Chromium, Cr	<= 0.0050 %	<= 0.0050 %	
Copper, Cu	<= 0.0020 %	<= 0.0020 %	
Iron, Fe	<= 0.0050 %	<= 0.0050 %	
Lead, Pb	<= 0.0020 %	<= 0.0020 %	
Magnesium, Mg	<= 0.0010 %	<= 0.0010 %	
Manganese, Mn	<= 0.0010 %	<= 0.0010 %	
Molybdenum, Mo	>= 99.95 %	>= 99.95 %	by difference
Nickel, Ni	<= 0.0020 %	<= 0.0020 %	
Silicon, Si	<= 0.0030 %	<= 0.0030 %	
Tin, Sn	<= 0.0030 %	<= 0.0030 %	
Titanium, Ti	<= 0.0020 %	<= 0.0020 %	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China