

## H.C. Starck Pure Molybdenum OMPP Pellets (99.8%)

Category : Metal , Nonferrous Metal , Molybdenum Alloy , Refractory Metal , Pure Element

### Material Notes:

Description of Product: This specification covers vacuum grade pressed and sintered molybdenum pellets, with a molybdenum content of 99.8% minimum. Pellet Size: approx. 1/2 inch by 3/4 inch by 1 inch (12.5 mm by 18 mm by 25 mm) Information provided by H.C. Starck.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_HC-Starck-Pure-Molybdenum-OMPP-Pellets-998.php](http://www.lookpolymers.com/polymer_HC-Starck-Pure-Molybdenum-OMPP-Pellets-998.php)

Physical Properties	Metric	English	Comments
Density	>= 7.00 g/cc	>= 0.253 lb/in <sup>3</sup>	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	0.0020 %	0.0020 %	typical
	<= 0.010 %	<= 0.010 %	
Calcium, Ca	0.0010 %	0.0010 %	typical
	<= 0.010 %	<= 0.010 %	
Carbon, C	0.0010 %	0.0010 %	Typical
	<= 0.0050 %	<= 0.0050 %	
Chromium, Cr	0.0030 %	0.0030 %	typical
	<= 0.020 %	<= 0.020 %	
Copper, Cu	<= 0.0010 %	<= 0.0010 %	typical
	<= 0.0050 %	<= 0.0050 %	
Iron, Fe	0.010 %	0.010 %	typical
	<= 0.030 %	<= 0.030 %	
Lead, Pb	<= 0.0010 %	<= 0.0010 %	
	<= 0.0010 %	<= 0.0010 %	typical
Magnesium, Mg	0.0010 %	0.0010 %	typical
	<= 0.010 %	<= 0.010 %	
Manganese, Mn	0.0010 %	0.0010 %	typical
	<= 0.0050 %	<= 0.0050 %	
Molybdenum, Mo			excluding gases

Component Elements Properties	$\geq 99.8\%$ Metric	$\geq 99.8\%$ English	Comments
Nickel, Ni	0.0010 %	0.0010 %	typical
	$\leq 0.030\%$	$\leq 0.030\%$	
Silicon, Si	0.012 %	0.012 %	typical
	$\leq 0.030\%$	$\leq 0.030\%$	
Tin, Sn	0.0030 %	0.0030 %	typical
	$\leq 0.0050\%$	$\leq 0.0050\%$	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China