

HP Alloys Alloy 718, 15% Cold Worked, Aged

Category : Metal , Nonferrous Metal , Nickel Alloy , Superalloy

Material Notes:

15% Cold Worked, Aged applies to tensile and/or hardness; other properties are typical of this alloy. Data provided by High Performance Alloys, Inc., Allvac, Inco Alloys International, and Haynes International.

Order this product through the following link:

http://www.lookpolymers.com/polymer_HP-Alloys-Alloy-718-15-Cold-Worked-Aged.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|--------------------------|----------|
| Density | 8.20 g/cc | 0.296 lb/in ³ | |

| Mechanical Properties | Metric | English | Comments |
|----------------------------|----------|------------|----------|
| Tensile Strength, Ultimate | 1517 MPa | 220000 psi | |
| Tensile Strength, Yield | 1420 MPa | 206000 psi | |
| Elongation at Break | 17 % | 17 % | |
| Reduction of Area | 40 % | 40 % | |
| Modulus of Elasticity | 200 GPa | 29000 ksi | |

| Thermal Properties | Metric | English | Comments |
|------------------------|--|---|----------|
| CTE, linear | 12.9 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ | 7.17 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ | |
| | @Temperature 20.0 - 100 $\text{Å}^\circ\text{C}$ | @Temperature 68.0 - 212 $\text{Å}^\circ\text{F}$ | |
| | 13.5 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ | 7.50 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ | |
| | @Temperature 25.0 - 200 $\text{Å}^\circ\text{C}$ | @Temperature 77.0 - 392 $\text{Å}^\circ\text{F}$ | |
| | 14.3 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ | 7.94 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ | |
| | @Temperature 25.0 - 500 $\text{Å}^\circ\text{C}$ | @Temperature 77.0 - 932 $\text{Å}^\circ\text{F}$ | |
| | 17.2 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ | 9.56 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ | |
| | @Temperature 25.0 - 900 $\text{Å}^\circ\text{C}$ | @Temperature 77.0 - 1650 $\text{Å}^\circ\text{F}$ | |
| Specific Heat Capacity | 0.435 J/g- $\text{Å}^\circ\text{C}$ | 0.104 BTU/lb- $\text{Å}^\circ\text{F}$ | |
| Thermal Conductivity | 11.4 W/m-K | 79.1 BTU-in/hr-ft Å^2 - $\text{Å}^\circ\text{F}$ | |
| Melting Point | 1260 - 1336 $\text{Å}^\circ\text{C}$ | 2300 - 2437 $\text{Å}^\circ\text{F}$ | |

| Thermal Properties | Metric | English | Comments |
|--------------------|----------|----------|----------|
| Liquidus | 1336 Â°C | 2437 Â°F | |

| Component Elements Properties | Metric | English | Comments |
|-------------------------------|---------------|---------------|----------|
| Aluminum, Al | 0.20 - 0.80 % | 0.20 - 0.80 % | |
| Boron, B | <= 0.0060 % | <= 0.0060 % | |
| Carbon, C | <= 0.080 % | <= 0.080 % | |
| Chromium, Cr | 17 - 21 % | 17 - 21 % | |
| Cobalt, Co | <= 1.0 % | <= 1.0 % | |
| Copper, Cu | <= 0.30 % | <= 0.30 % | |
| Iron, Fe | 17 % | 17 % | |
| Manganese, Mn | <= 0.35 % | <= 0.35 % | |
| Molybdenum, Mo | 2.8 - 3.3 % | 2.8 - 3.3 % | |
| Nickel, Ni | 50 - 55 % | 50 - 55 % | |
| Niobium, Nb (Columbium, Cb) | 4.75 - 5.5 % | 4.75 - 5.5 % | |
| Phosphorous, P | <= 0.015 % | <= 0.015 % | |
| Silicon, Si | <= 0.35 % | <= 0.35 % | |
| Sulfur, S | <= 0.015 % | <= 0.015 % | |
| Titanium, Ti | 0.65 - 1.15 % | 0.65 - 1.15 % | |

| Electrical Properties | Metric | English | Comments |
|------------------------|-----------------|-----------------|----------------------------|
| Electrical Resistivity | 0.000123 ohm-cm | 0.000123 ohm-cm | |
| Magnetic Permeability | 1.0011 | 1.0011 | at 200 oersted (15.9 kA/m) |
| Curie Temperature | -112 Â°C | -170 Â°F | |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China