

HP Alloys Alloy 718, 30% Cold Worked, Aged

Category : Metal , Nonferrous Metal , Nickel Alloy , Superalloy

Material Notes:

30% Cold Worked, Aged applies to tensile and/or hardness; other properties are typical of this alloy. Data provided by High Performance Alloys, Inc., Allvac, Inco Alloys International, and Haynes International.

Order this product through the following link:

http://www.lookpolymers.com/polymer_HP-Alloys-Alloy-718-30-Cold-Worked-Aged.php

Physical Properties	Metric	English	Comments
Density	8.20 g/cc	0.296 lb/in ³	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	1655 MPa	240000 psi	
Tensile Strength, Yield	1565 MPa	227000 psi	
Elongation at Break	10 %	10 %	
Reduction of Area	25 %	25 %	
Modulus of Elasticity	200 GPa	29000 ksi	

Thermal Properties	Metric	English	Comments
CTE, linear	12.9 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	7.17 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
	@Temperature 20.0 - 100 $\text{Å}^\circ\text{C}$	@Temperature 68.0 - 212 $\text{Å}^\circ\text{F}$	
	13.5 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	7.50 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
	@Temperature 25.0 - 200 $\text{Å}^\circ\text{C}$	@Temperature 77.0 - 392 $\text{Å}^\circ\text{F}$	
	14.3 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	7.94 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
	@Temperature 25.0 - 500 $\text{Å}^\circ\text{C}$	@Temperature 77.0 - 932 $\text{Å}^\circ\text{F}$	
	17.2 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	9.56 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
	@Temperature 25.0 - 900 $\text{Å}^\circ\text{C}$	@Temperature 77.0 - 1650 $\text{Å}^\circ\text{F}$	
Specific Heat Capacity	0.435 J/g- $\text{Å}^\circ\text{C}$	0.104 BTU/lb- $\text{Å}^\circ\text{F}$	
Thermal Conductivity	11.4 W/m-K	79.1 BTU-in/hr-ft Å^2 - $\text{Å}^\circ\text{F}$	
Melting Point	1260 - 1336 $\text{Å}^\circ\text{C}$	2300 - 2437 $\text{Å}^\circ\text{F}$	

Thermal Properties	Metric	English	Comments
Liquidus	1336 Â°C	2437 Â°F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	0.20 - 0.80 %	0.20 - 0.80 %	
Boron, B	<= 0.0060 %	<= 0.0060 %	
Carbon, C	<= 0.080 %	<= 0.080 %	
Chromium, Cr	17 - 21 %	17 - 21 %	
Cobalt, Co	<= 1.0 %	<= 1.0 %	
Copper, Cu	<= 0.30 %	<= 0.30 %	
Iron, Fe	17 %	17 %	
Manganese, Mn	<= 0.35 %	<= 0.35 %	
Molybdenum, Mo	2.8 - 3.3 %	2.8 - 3.3 %	
Nickel, Ni	50 - 55 %	50 - 55 %	
Niobium, Nb (Columbium, Cb)	4.75 - 5.5 %	4.75 - 5.5 %	
Phosphorous, P	<= 0.015 %	<= 0.015 %	
Silicon, Si	<= 0.35 %	<= 0.35 %	
Sulfur, S	<= 0.015 %	<= 0.015 %	
Titanium, Ti	0.65 - 1.15 %	0.65 - 1.15 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.000123 ohm-cm	0.000123 ohm-cm	
Magnetic Permeability	1.0011	1.0011	at 200 oersted (15.9 kA/m)
Curie Temperature	-112 Â°C	-170 Â°F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China