

Haynes 556® alloy, hot rolled, solution annealed plate, 6.4-12.7 mm (1/2 in.) thick

Category : Metal , Superalloy , Iron Base

Material Notes:

Effective resistance to sulfidizing, carburizing, and chlorine-bearing environments at high temperature; good oxidation resistance, fabricability, and excellent high-temperature strength; resists corrosion by molten chloride salts and is resistant to corrosion from molten zinc. Excellent forming and welding characteristics. Applications include tubing and structural members in municipal and industrial waste incinerators, rotary calciners and kilns for minerals processing, and non-rotating components in land-based gas turbines burning low-grade fuels; carbon regenerators, and in processes involving high-sulfur petroleum feedstocks; widely used for hot-dip galvanizing fixtures, spinners, and baskets, high speed furnace fans, air preheaters of diesel engines, the inner covers of coil annealing furnaces, and various high temperature applications in the aerospace industry. Data provided by the manufacturer, Haynes International, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Haynes-556-alloy-hot-rolled-solution-annealed-plate-64-127-mm-12-in-thick.php

Physical Properties	Metric	English	Comments
Density	8.23 g/cc	0.297 lb/in³	at RT

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	805 MPa	117000 psi	
	110 MPa	16000 psi	
	@Temperature 1095 °C	@Temperature 2003 °F	
	210 MPa	30500 psi	
	@Temperature 980 °C	@Temperature 1800 °F	
	340 MPa	49300 psi	
	@Temperature 870 °C	@Temperature 1600 °F	
	470 MPa	68200 psi	
	@Temperature 760 °C	@Temperature 1400 °F	
	575 MPa	83400 psi	
	@Temperature 650 °C	@Temperature 1200 °F	
	625 MPa	90600 psi	
	@Temperature 540 °C	@Temperature 1000 °F	

Mechanical Properties	375 MPa Metric	54400 psi English	Comments
Tensile Strength Yield	@Strain 0.200 %	@Strain 0.200 %	
	60.0 MPa	8700 psi	
	@Strain 0.200 %, Temperature 1095 °C	@Strain 0.200 %, Temperature 2003 °F	
	130 MPa	18900 psi	
	@Strain 0.200 %, Temperature 980 °C	@Strain 0.200 %, Temperature 1800 °F	
	190 MPa	27600 psi	
	@Strain 0.200 %, Temperature 870 °C	@Strain 0.200 %, Temperature 1600 °F	
	200 MPa	29000 psi	
	@Strain 0.200 %, Temperature 760 °C	@Strain 0.200 %, Temperature 1400 °F	
	210 MPa	30500 psi	
	@Strain 0.200 %, Temperature 540 °C	@Strain 0.200 %, Temperature 1000 °F	
	210 MPa	30500 psi	
	@Strain 0.200 %, Temperature 650 °C	@Strain 0.200 %, Temperature 1200 °F	
Elongation at Break	51.4 %	51.4 %	in 50.8 mm
	52.6 %	52.6 %	
	@Temperature 760 °C	@Temperature 1400 °F	in 50.8 mm
	57.4 %	57.4 %	
	@Temperature 650 °C	@Temperature 1200 °F	in 50.8 mm
	60.3 %	60.3 %	
	@Temperature 540 °C	@Temperature 1000 °F	in 50.8 mm
	69.1 %	69.1 %	
	@Temperature 870 °C	@Temperature 1600 °F	in 50.8 mm
	83.9 %	83.9 %	
	@Temperature 980 °C	@Temperature 1800 °F	in 50.8 mm
	95.2 %	95.2 %	

Mechanical Properties	Metric Temperature 1095 °C	English Temperature 2003 °F	in 50.8 mm Comments
Modulus of Elasticity	205 GPa	29700 ksi	RT
	138 GPa	20000 ksi	
	@Temperature 1000 °C	@Temperature 1830 °F	
	143 GPa	20700 ksi	
	@Temperature 900 °C	@Temperature 1650 °F	
	148 GPa	21500 ksi	
	@Temperature 800 °C	@Temperature 1470 °F	
	155 GPa	22500 ksi	
	@Temperature 700 °C	@Temperature 1290 °F	
	164 GPa	23800 ksi	
	@Temperature 600 °C	@Temperature 1110 °F	
	172 GPa	24900 ksi	
	@Temperature 500 °C	@Temperature 932 °F	
	179 GPa	26000 ksi	
	@Temperature 400 °C	@Temperature 752 °F	
	187 GPa	27100 ksi	
	@Temperature 300 °C	@Temperature 572 °F	
	195 GPa	28300 ksi	
	@Temperature 200 °C	@Temperature 392 °F	
	200 GPa	29000 ksi	
	@Temperature 100 °C	@Temperature 212 °F	
Charpy Impact	240 J	177 ft-lb	Samples did not break. Average of 4 or more tests.

Thermal Properties	Metric	English	Comments
CTE, linear	14.7 $\mu\text{m}/\text{m-}^\circ\text{C}$	8.17 $\mu\text{in/in-}^\circ\text{F}$	
	@Temperature 25.0 - 100 °C	@Temperature 77.0 - 212 °F	
	14.9 $\mu\text{m}/\text{m-}^\circ\text{C}$	8.28 $\mu\text{in/in-}^\circ\text{F}$	

Thermal Properties	Metric @Temperature 25.0 - 200 °C	English @Temperature 77.0 - 392 °F	Comments
	15.1 Åµm/m-Å°C	8.39 Åµin/in-Å°F	
	@Temperature 25.0 - 300 °C	@Temperature 77.0 - 572 °F	
	15.4 Åµm/m-Å°C	8.56 Åµin/in-Å°F	
	@Temperature 25.0 - 400 °C	@Temperature 77.0 - 752 °F	
	15.7 Åµm/m-Å°C	8.72 Åµin/in-Å°F	
	@Temperature 25.0 - 500 °C	@Temperature 77.0 - 932 °F	
	16.1 Åµm/m-Å°C	8.94 Åµin/in-Å°F	
	@Temperature 25.0 - 600 °C	@Temperature 77.0 - 1110 °F	
	16.4 Åµm/m-Å°C	9.11 Åµin/in-Å°F	
	@Temperature 25.0 - 700 °C	@Temperature 77.0 - 1290 °F	
	16.7 Åµm/m-Å°C	9.28 Åµin/in-Å°F	
	@Temperature 25.0 - 800 °C	@Temperature 77.0 - 1470 °F	
	17.0 Åµm/m-Å°C	9.44 Åµin/in-Å°F	
	@Temperature 25.0 - 900 °C	@Temperature 77.0 - 1650 °F	
	17.1 Åµm/m-Å°C	9.50 Åµin/in-Å°F	
	@Temperature 25.0 - 1000 °C	@Temperature 77.0 - 1830 °F	
Specific Heat Capacity	0.464 J/g-Å°C	0.111 BTU/lb-Å°F	RT
	0.475 J/g-Å°C	0.114 BTU/lb-Å°F	
	@Temperature 100 °C	@Temperature 212 °F	
	0.493 J/g-Å°C	0.118 BTU/lb-Å°F	
	@Temperature 200 °C	@Temperature 392 °F	
	0.508 J/g-Å°C	0.121 BTU/lb-Å°F	
	@Temperature 300 °C	@Temperature 572 °F	
	0.523 J/g-Å°C	0.125 BTU/lb-Å°F	
	@Temperature 400 °C	@Temperature 752 °F	

Thermal Properties	Metric	English	Comments
	0.638 J/g-Â°C	0.129 BTU/lb-Â°F	
	@Temperature 500 Â°C	@Temperature 932 Â°F	
	0.552 J/g-Â°C	0.132 BTU/lb-Â°F	
	@Temperature 600 Â°C	@Temperature 1110 Â°F	
	0.561 J/g-Â°C	0.134 BTU/lb-Â°F	
	@Temperature 700 Â°C	@Temperature 1290 Â°F	
	0.570 J/g-Â°C	0.136 BTU/lb-Â°F	
	@Temperature 800 Â°C	@Temperature 1470 Â°F	
	0.595 J/g-Â°C	0.142 BTU/lb-Â°F	
	@Temperature 900 Â°C	@Temperature 1650 Â°F	
	0.618 J/g-Â°C	0.148 BTU/lb-Â°F	
	@Temperature 1000 Â°C	@Temperature 1830 Â°F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000952 ohm-cm	0.0000952 ohm-cm	RT
	0.0000986 ohm-cm	0.0000986 ohm-cm	
	@Temperature 100 Â°C	@Temperature 212 Â°F	
	0.0001026 ohm-cm	0.0001026 ohm-cm	
	@Temperature 200 Â°C	@Temperature 392 Â°F	
	0.0001065 ohm-cm	0.0001065 ohm-cm	
	@Temperature 300 Â°C	@Temperature 572 Â°F	
	0.0001095 ohm-cm	0.0001095 ohm-cm	
	@Temperature 400 Â°C	@Temperature 752 Â°F	
	0.0001125 ohm-cm	0.0001125 ohm-cm	
	@Temperature 500 Â°C	@Temperature 932 Â°F	
	0.0001151 ohm-cm	0.0001151 ohm-cm	
	@Temperature 600 Â°C	@Temperature 1110 Â°F	
	0.0001172 ohm-cm	0.0001172 ohm-cm	
	@Temperature 700 Â°C	@Temperature 1290 Â°F	

Electrical Properties	Metric 0.000119 ohm-cm	English 19 ohm-cm	Comments
	@Temperature 800 °C	@Temperature 1470 °F	
	0.0001207 ohm-cm	0.0001207 ohm-cm	
	@Temperature 900 °C	@Temperature 1650 °F	
	0.0001223 ohm-cm	0.0001223 ohm-cm	
	@Temperature 1000 °C	@Temperature 1830 °F	
	0.0001237 ohm-cm	0.0001237 ohm-cm	
	@Temperature 1100 °C	@Temperature 2010 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China