

## Haynes 625 alloy, hot rolled and 1050Â°C mill-annealed plate

Category : Metal , Nonferrous Metal , Nickel Alloy , Superalloy

### Material Notes:

Cb and Ta content 3.7% combined. Excellent strength up to 816Â°C, good oxidation resistance and aqueous corrosion, excellent forming and welding characteristics. Applications include a variety of high-temperature aerospace, chemical process industry and power industry uses. Widely used in sea water and power plant scrubber applications. Data provided by the manufacturer, Haynes International, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Haynes-625-alloy-hot-rolled-and-1050C-mill-annealed-plate.php](http://www.lookpolymers.com/polymer_Haynes-625-alloy-hot-rolled-and-1050C-mill-annealed-plate.php)

Physical Properties	Metric	English	Comments
Density	8.44 g/cc	0.305 lb/inÂ³	at RT

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	895 MPa	130000 psi	
Tensile Strength, Yield	490 MPa @Strain 0.200 %	71100 psi @Strain 0.200 %	
Elongation at Break	43.8 %	43.8 %	in 50.8 mm
Modulus of Elasticity	208 GPa	30200 ksi	RT
	126 GPa @Temperature 1000 Â°C	18300 ksi @Temperature 1830 Â°F	
	142 GPa @Temperature 900 Â°C	20600 ksi @Temperature 1650 Â°F	
	153 GPa @Temperature 800 Â°C	22200 ksi @Temperature 1470 Â°F	
	163 GPa @Temperature 700 Â°C	23600 ksi @Temperature 1290 Â°F	
	171 GPa @Temperature 600 Â°C	24800 ksi @Temperature 1110 Â°F	
	179 GPa @Temperature 500 Â°C	26000 ksi @Temperature 932 Â°F	

Mechanical Properties	186 GPa Metric	27000 ksi English	Comments
	@Temperature 400 Â°C	@Temperature 752 Â°F	
	192 GPa	27800 ksi	
	@Temperature 300 Â°C	@Temperature 572 Â°F	
	199 GPa	28900 ksi	
	@Temperature 200 Â°C	@Temperature 392 Â°F	
	201 GPa	29200 ksi	
	@Temperature 100 Â°C	@Temperature 212 Â°F	

Thermal Properties	Metric	English	Comments
CTE, linear	12.8 Âµm/m-Â°C	7.11 Âµin/in-Â°F	
	@Temperature 25.0 - 100 Â°C	@Temperature 77.0 - 212 Â°F	
	13.1 Âµm/m-Â°C	7.28 Âµin/in-Â°F	
	@Temperature 25.0 - 200 Â°C	@Temperature 77.0 - 392 Â°F	
	13.4 Âµm/m-Â°C	7.44 Âµin/in-Â°F	
	@Temperature 25.0 - 300 Â°C	@Temperature 77.0 - 572 Â°F	
	13.8 Âµm/m-Â°C	7.67 Âµin/in-Â°F	
	@Temperature 25.0 - 400 Â°C	@Temperature 77.0 - 752 Â°F	
	14.2 Âµm/m-Â°C	7.89 Âµin/in-Â°F	
	@Temperature 25.0 - 500 Â°C	@Temperature 77.0 - 932 Â°F	
	14.8 Âµm/m-Â°C	8.22 Âµin/in-Â°F	
	@Temperature 25.0 - 600 Â°C	@Temperature 77.0 - 1110 Â°F	
	15.4 Âµm/m-Â°C	8.56 Âµin/in-Â°F	
	@Temperature 25.0 - 700 Â°C	@Temperature 77.0 - 1290 Â°F	
	16.0 Âµm/m-Â°C	8.89 Âµin/in-Â°F	
	@Temperature 25.0 - 800 Â°C	@Temperature 77.0 - 1470 Â°F	
	16.7 Âµm/m-Â°C	9.28 Âµin/in-Â°F	
	@Temperature 25.0 -	@Temperature 77.0 -	

Thermal Properties	900 °C Metric	1650 °F English	Comments
	17.4 Åµm/m-Å°C	9.67 Åµin/in-Å°F	
	@Temperature 25.0 - 1000 Å°C	@Temperature 77.0 - 1830 Å°F	
Specific Heat Capacity	0.410 J/g-Å°C	0.0980 BTU/lb-Å°F	RT
	0.428 J/g-Å°C	0.102 BTU/lb-Å°F	
	@Temperature 100 Å°C	@Temperature 212 Å°F	
	0.455 J/g-Å°C	0.109 BTU/lb-Å°F	
	@Temperature 200 Å°C	@Temperature 392 Å°F	
	0.477 J/g-Å°C	0.114 BTU/lb-Å°F	
	@Temperature 300 Å°C	@Temperature 572 Å°F	
	0.503 J/g-Å°C	0.120 BTU/lb-Å°F	
	@Temperature 400 Å°C	@Temperature 752 Å°F	
	0.527 J/g-Å°C	0.126 BTU/lb-Å°F	
	@Temperature 500 Å°C	@Temperature 932 Å°F	
	0.552 J/g-Å°C	0.132 BTU/lb-Å°F	
	@Temperature 600 Å°C	@Temperature 1110 Å°F	
	0.576 J/g-Å°C	0.138 BTU/lb-Å°F	
	@Temperature 700 Å°C	@Temperature 1290 Å°F	
	0.600 J/g-Å°C	0.143 BTU/lb-Å°F	
	@Temperature 800 Å°C	@Temperature 1470 Å°F	
	0.625 J/g-Å°C	0.149 BTU/lb-Å°F	
	@Temperature 900 Å°C	@Temperature 1650 Å°F	
	0.648 J/g-Å°C	0.155 BTU/lb-Å°F	
	@Temperature 1000 Å°C	@Temperature 1830 Å°F	
Thermal Conductivity	9.80 W/m-K	68.0 BTU-in/hr-ftÅ²-Å°F	RT
	10.9 W/m-K	75.6 BTU-in/hr-ftÅ²-Å°F	
	@Temperature 100 Å°C	@Temperature 212 Å°F	

Thermal Properties	Metric	English	Comments
	@Temperature 200 Â°C	@Temperature 392 Â°F	
	13.9 W/m-K @Temperature 300 Â°C	96.5 BTU-in/hr-ftÂ²-Â°F @Temperature 572 Â°F	
	15.3 W/m-K @Temperature 400 Â°C	106 BTU-in/hr-ftÂ²-Â°F @Temperature 752 Â°F	
	16.9 W/m-K @Temperature 500 Â°C	117 BTU-in/hr-ftÂ²-Â°F @Temperature 932 Â°F	
	18.3 W/m-K @Temperature 600 Â°C	127 BTU-in/hr-ftÂ²-Â°F @Temperature 1110 Â°F	
	19.8 W/m-K @Temperature 700 Â°C	137 BTU-in/hr-ftÂ²-Â°F @Temperature 1290 Â°F	
	21.5 W/m-K @Temperature 800 Â°C	149 BTU-in/hr-ftÂ²-Â°F @Temperature 1470 Â°F	
	23.4 W/m-K @Temperature 900 Â°C	162 BTU-in/hr-ftÂ²-Â°F @Temperature 1650 Â°F	
	25.6 W/m-K @Temperature 1000 Â°C	178 BTU-in/hr-ftÂ²-Â°F @Temperature 1830 Â°F	
Melting Point	1290 - 1350 Â°C	2350 - 2460 Â°F	
Solidus	1290 Â°C	2350 Â°F	
Liquidus	1350 Â°C	2460 Â°F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	<= 0.40 %	<= 0.40 %	
Carbon, C	<= 0.10 %	<= 0.10 %	
Chromium, Cr	21 %	21 %	
Cobalt, Co	<= 1.0 %	<= 1.0 %	
Iron, Fe	<= 5.0 %	<= 5.0 %	

Component Elements Properties	Metric	English	Comments
Manganese, Mn	<= 0.30 %	<= 0.30 %	
Molybdenum, Mo	9.0 %	9.0 %	
Nickel, Ni	62 %	62 %	As Remainder

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.000129 ohm-cm	0.000129 ohm-cm	RT
	0.000132 ohm-cm	0.000132 ohm-cm	
	@Temperature 100 Â°C	@Temperature 212 Â°F	
	0.000134 ohm-cm	0.000134 ohm-cm	
	@Temperature 200 Â°C	@Temperature 392 Â°F	
	0.000135 ohm-cm	0.000135 ohm-cm	
	@Temperature 300 Â°C	@Temperature 572 Â°F	
	0.000135 ohm-cm	0.000135 ohm-cm	
	@Temperature 1000 Â°C	@Temperature 1830 Â°F	
	0.000136 ohm-cm	0.000136 ohm-cm	
	@Temperature 900 Â°C	@Temperature 1650 Â°F	
	0.000136 ohm-cm	0.000136 ohm-cm	
	@Temperature 400 Â°C	@Temperature 752 Â°F	
	0.000137 ohm-cm	0.000137 ohm-cm	
	@Temperature 500 Â°C	@Temperature 932 Â°F	
	0.000137 ohm-cm	0.000137 ohm-cm	
	@Temperature 800 Â°C	@Temperature 1470 Â°F	
	0.000138 ohm-cm	0.000138 ohm-cm	
	@Temperature 600 Â°C	@Temperature 1110 Â°F	
	0.000138 ohm-cm	0.000138 ohm-cm	
	@Temperature 700 Â°C	@Temperature 1290 Â°F	

Contact Songhan Plastic Technology Co.,Ltd.

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**