

Haynes Hastelloy® C-22® alloy, transverse, GTAW short arc weldment, plate

Category : Metal , Nonferrous Metal , Nickel Alloy , Superalloy

Material Notes:

HASTELLOY® C-22® alloy is a nickel-chromium-molybdenum-tungsten alloy with excellent overall corrosion resistance compared to other Ni-Cr-Mo alloys, including HASTELLOY C-276 and C-4 alloys and alloy 625. C-22 alloy has outstanding resistance to pitting, crevice corrosion, and stress corrosion cracking. It has excellent resistance to oxidizing aqueous media including wet chlorine and mixtures containing nitric acid or oxidizing acids with chloride ions. C-22 alloy offers optimum resistance to environments where reducing and oxidizing conditions are encountered in process streams. Because of such versatility it can be used where "upset" conditions are likely to occur or in multi-purpose plants. C-22 alloy has exceptional resistance to a wide variety of chemical process environments, including strong oxidizers such as ferric and cupric chlorides, chlorine, hot contaminated solutions (organic and inorganic), formic and acetic acids, acetic anhydride, and seawater and brine solutions. C-22 alloy resists the formation of grain-boundary precipitates in the weld heat-affected zone, thus making it suitable for most chemical process applications in the as-welded condition. Product Forms: C-22 alloy is available in most common product forms: plate, sheet, strip, billet, bar, wire, covered electrodes, pipe, and tubing. Applications: Acetic Acid/Acetic Anhydride Acid Etching Cellophane Manufacturing Chlorination Systems Complex Acid Mixtures Electro-Galvanizing Rolls Expansion Bellows Flue Gas Scrubber Systems Geothermal Wells HF Furnace Scrubbers Incineration Scrubber Systems Nuclear Fuel Reprocessing Pesticide Production Phosphoric Acid Production Pickling Systems Plate Heat Exchangers Selective Leaching Systems SO2 Cooling Towers Sulfonation Systems Tubular Heat Exchangers Weld Overlay-Valves Data provided by the manufacturer, Haynes International, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Haynes-Hastelloy-C-22-alloy-transverse-GTAW-short-arc-weldment-plate.php

Physical Properties	Metric	English	Comments
Density	8.69 g/cc	0.314 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell B	93	93	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	95	95	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Tensile Strength, Ultimate	434 MPa	62900 psi	
	@Thickness 12.7 mm, Temperature 760 °C	@Thickness 0.500 in, Temperature 1400 °F	
	565 MPa	81900 psi	
	@Thickness 12.7 mm, Temperature 538 °C	@Thickness 0.500 in, Temperature 1000 °F	
	586 MPa	85000 psi	
	@Thickness 6.35 mm,	@Thickness 0.250 in,	

Mechanical Properties	Temperature 538 °C Metric	Temperature 1000 °F English	Comments
	752 MPa	109000 psi	
	@Thickness 12.7 mm, Temperature 20.0 °C	@Thickness 0.500 in, Temperature 68.0 °F	
	765 MPa	111000 psi	
	@Thickness 6.35 mm, Temperature 20.0 °C	@Thickness 0.250 in, Temperature 68.0 °F	
Tensile Strength, Yield	269 MPa	39000 psi	0.2% offset
	@Thickness 6.35 mm, Temperature 538 °C	@Thickness 0.250 in, Temperature 1000 °F	
	269 MPa	39000 psi	0.2% offset
	@Thickness 12.7 mm, Temperature 760 °C	@Thickness 0.500 in, Temperature 1400 °F	
	310 MPa	45000 psi	0.2% offset
	@Thickness 12.7 mm, Temperature 538 °C	@Thickness 0.500 in, Temperature 1000 °F	
	393 MPa	57000 psi	0.2% offset
	@Thickness 6.35 mm, Temperature 20.0 °C	@Thickness 0.250 in, Temperature 68.0 °F	
	434 MPa	62900 psi	0.2% offset
	@Thickness 12.7 mm, Temperature 20.0 °C	@Thickness 0.500 in, Temperature 68.0 °F	
Elongation at Break	25 %	25 %	in 50.8 mm
	@Thickness 12.7 mm, Temperature 760 °C	@Thickness 0.500 in, Temperature 1400 °F	
	38 %	38 %	in 50.8 mm
	@Thickness 12.7 mm, Temperature 538 °C	@Thickness 0.500 in, Temperature 1000 °F	
	38 %	38 %	in 50.8 mm
	@Thickness 12.7 mm, Temperature 20.0 °C	@Thickness 0.500 in, Temperature 68.0 °F	
	43 %	43 %	in 50.8 mm
	@Thickness 6.35 mm, Temperature 20.0 °C	@Thickness 0.250 in, Temperature 68.0 °F	
	46 %	46 %	in 50.8 mm
	@Thickness 6.35 mm, Temperature 538 °C	@Thickness 0.250 in, Temperature 1000 °F	

heat-treated at 1121°C (2050°F),

Modulus of Elasticity Mechanical Properties	206 GPa Metric	29900 ksi English	rapid quenched, plate Comments
	145 GPa @Temperature 982 °C	21000 ksi @Temperature 1800 °F	heat-treated at 1121°C (2050°F), rapid quenched, plate
	154 GPa @Temperature 871 °C	22300 ksi @Temperature 1600 °F	heat-treated at 1121°C (2050°F), rapid quenched, plate
	163 GPa @Temperature 760 °C	23600 ksi @Temperature 1400 °F	heat-treated at 1121°C (2050°F), rapid quenched, plate
	171 GPa @Temperature 649 °C	24800 ksi @Temperature 1200 °F	heat-treated at 1121°C (2050°F), rapid quenched, plate
	177 GPa @Temperature 538 °C	25700 ksi @Temperature 1000 °F	heat-treated at 1121°C (2050°F), rapid quenched, plate
	183 GPa @Temperature 427 °C	26500 ksi @Temperature 801 °F	heat-treated at 1121°C (2050°F), rapid quenched, plate
	190 GPa @Temperature 316 °C	27600 ksi @Temperature 601 °F	heat-treated at 1121°C (2050°F), rapid quenched, plate
	196 GPa @Temperature 204 °C	28400 ksi @Temperature 399 °F	heat-treated at 1121°C (2050°F), rapid quenched, plate
	203 GPa @Temperature 93.0 °C	29400 ksi @Temperature 199 °F	heat-treated at 1121°C (2050°F), rapid quenched, plate

Thermal Properties	Metric	English	Comments
CTE, linear	12.4 µm/m-°C @Temperature 24.0 - 204 °C	6.89 µin/in-°F @Temperature 75.2 - 399 °F	
	12.4 µm/m-°C @Temperature 24.0 - 93.0 °C	6.89 µin/in-°F @Temperature 75.2 - 199 °F	
	12.6 µm/m-°C @Temperature 24.0 - 316 °C	7.00 µin/in-°F @Temperature 75.2 - 601 °F	
	13.3 µm/m-°C @Temperature 24.0 - 427 °C	7.39 µin/in-°F @Temperature 75.2 - 801 °F	
	13.9 µm/m-°C	7.72 µin/in-°F	

Thermal Properties	Metric	English	Comments
	@Temperature 24.0 - 538 °C	@Temperature 75.2 - 1000 °F	
	14.6 µm/m-°C	8.11 µin/in-°F	
	@Temperature 24.0 - 649 °C	@Temperature 75.2 - 1200 °F	
	15.3 µm/m-°C	8.50 µin/in-°F	
	@Temperature 24.0 - 760 °C	@Temperature 75.2 - 1400 °F	
	15.8 µm/m-°C	8.78 µin/in-°F	
	@Temperature 24.0 - 871 °C	@Temperature 75.2 - 1600 °F	
	16.2 µm/m-°C	9.00 µin/in-°F	
	@Temperature 24.0 - 982 °C	@Temperature 75.2 - 1800 °F	
Specific Heat Capacity	0.414 J/g-°C	0.0989 BTU/lb-°F	
	@Temperature 52.0 °C	@Temperature 126 °F	
	0.423 J/g-°C	0.101 BTU/lb-°F	
	@Temperature 100 °C	@Temperature 212 °F	
	0.444 J/g-°C	0.106 BTU/lb-°F	
	@Temperature 200 °C	@Temperature 392 °F	
	0.460 J/g-°C	0.110 BTU/lb-°F	
	@Temperature 300 °C	@Temperature 572 °F	
	0.476 J/g-°C	0.114 BTU/lb-°F	
	@Temperature 400 °C	@Temperature 752 °F	
	0.489 J/g-°C	0.117 BTU/lb-°F	
	@Temperature 500 °C	@Temperature 932 °F	
	0.514 J/g-°C	0.123 BTU/lb-°F	
	@Temperature 600 °C	@Temperature 1110 °F	
Thermal Conductivity	10.1 W/m-K	70.1 BTU-in/hr-ft ² -°F	
	@Temperature 48.0 °C	@Temperature 118 °F	
	11.1 W/m-K	77.0 BTU-in/hr-ft ² -°F	
	@Temperature 100 °C	@Temperature 212 °F	
	13.4 W/m-K	93.0 BTU-in/hr-ft ² -°F	

Thermal Properties	@Temperature 200 °C Metric	@Temperature 392 °F English	Comments
	15.5 W/m-K	108 BTU-in/hr-ft ² -°F	
	@Temperature 300 °C	@Temperature 572 °F	
	17.5 W/m-K	121 BTU-in/hr-ft ² -°F	
	@Temperature 400 °C	@Temperature 752 °F	
	19.5 W/m-K	135 BTU-in/hr-ft ² -°F	
	@Temperature 500 °C	@Temperature 932 °F	
	21.3 W/m-K	148 BTU-in/hr-ft ² -°F	
	@Temperature 600 °C	@Temperature 1110 °F	
Melting Point	1357 - 1399 °C	2475 - 2550 °F	
Solidus	1357 °C	2475 °F	
Liquidus	1399 °C	2550 °F	

Component Elements Properties	Metric	English	Comments
Carbon, C	<= 0.010 %	<= 0.010 %	
Chromium, Cr	22 %	22 %	
Cobalt, Co	<= 2.5 %	<= 2.5 %	
Iron, Fe	3.0 %	3.0 %	
Manganese, Mn	<= 0.50 %	<= 0.50 %	
Molybdenum, Mo	13 %	13 %	
Nickel, Ni	56 %	56 %	
Silicon, Si	<= 0.080 %	<= 0.080 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.000114 ohm-cm	0.000114 ohm-cm	
	@Temperature 24.0 °C	@Temperature 75.2 °F	
	0.000123 ohm-cm	0.000123 ohm-cm	
	@Temperature 100 °C	@Temperature 212 °F	
	0.000124 ohm-cm	0.000124 ohm-cm	
	@Temperature 200 °C	@Temperature 392 °F	
	0.000125 ohm-cm	0.000125 ohm-cm	

Electrical Properties	Metric	English	Comments
	@Temperature 300 °C	@Temperature 572 °F	
	0.000126 ohm-cm	0.000126 ohm-cm	
	@Temperature 400 °C	@Temperature 752 °F	
	0.000127 ohm-cm	0.000127 ohm-cm	
	@Temperature 500 °C	@Temperature 932 °F	
	0.000128 ohm-cm	0.000128 ohm-cm	
	@Temperature 600 °C	@Temperature 1110 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China