

Haynes Hastelloy® C-22HS™ Nickel Alloy Synergic Gas Metal Arc Welded (GMAW) Plate

Category : Metal , Nonferrous Metal , Nickel Alloy

Material Notes:

Outstanding Corrosion Resistance, High Strength HASTELLOY® C-22HSTM alloy is corrosion-resistant, nickel-chromium-molybdenum alloy which can be heat treated to obtain a strength approximately double that of other C-type alloys. Importantly, the corrosion resistance and ductility of the alloy remain excellent when in the high strength condition. In addition to its high uniform corrosion resistance in oxidizing as well as reducing environments, the as-heat treated C-22HS alloy possesses high resistance to chloride-induced pitting and crevice corrosion attack. C-22HS alloy is available in the form of plate, sheet, strip, billet, bar, wire, pipe, and tube. Heat Treatment: The high strength of C-22HS alloy is derived from the formation of strengthening particles of Ni₂(Mo,Cr) which form during the patented two-step age-hardening heat treatment. The approximately 48 hour heat treatment, 1300°F (705°C) FC to 1125°F (605°C)/32 hours/AC, is described in more detail on page 14. Solution Annealed and Filler Wire Applications: C-22HS alloy may also be considered for applications which do not require the high strength imparted by the heat treatment. In the annealed condition, C-22HS alloy has even higher corrosion-resistance, particularly with regard to localized corrosive attack. This localized attack resistance also makes the alloy an attractive candidate as a general-purpose filler metal or weld overlay. Applications: Agitators and blenders Shafting Fan blades and hubs Fasteners Springs Valves Dies Screws Wellhead parts Rings and gaskets Heat Treatment: Wrought forms of C-22HS alloy are furnished in the solution annealed condition, unless otherwise specified. The standard solution annealing treatment consists of heating to 1975°F (1080°C) followed by rapid air-cooling or water quenching. Parts which have been hot formed should be solution annealed prior to final fabrication or installation. To use the alloy in the high-strength condition, it is necessary to age-harden using a two step treatment of 1300°F (705°C) for 16 hours, furnace cooling to 1125°F (605°C) and holding at that temperature for 32 hours, followed by an air cool. Cold or hot-worked structures should normally be given a full solution anneal prior to performing the age-hardening treatment. Forming: C-22HS alloy has excellent forming characteristics, and cold forming is the preferred method of shaping. The alloy can be easily cold worked due to its good ductility. The alloy is generally stiffer than the austenitic stainless steels; therefore more energy is required during cold forming. For further information on the fabrication of C-type alloys, please consult publication H-2010. Machining: C-22HS alloy may be machined in either the solution annealed or age-hardened condition. Carbide or ceramic tools are recommended. For use in the age-hardened condition, it is suggested to rough machine in the annealed condition. After performing the age-hardening heat treatment, light machining may be performed to achieve desired final dimensions. Tensile and impact properties reported are for transverse synergic gas metal arc welded plate specimens. Other properties are typical of the alloy. Data provided by the manufacturer, Haynes International, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Haynes-Hastelloy-C-22HS-Nickel-Alloy-Synergic-Gas-Metal-Arc-Welded-GMAW-Plate.php

Physical Properties	Metric	English	Comments
Density	8.60 g/cc	0.311 lb/in ³	annealed
	8.64 g/cc	0.312 lb/in ³	age-hardened

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	780 MPa	113000 psi	as welded
	@Thickness 25.4 mm,	@Thickness 1.00 in,	

Mechanical Properties	Temperature 25.0 °C Metric	Temperature 77.0 °F English	Comments
	785 MPa	114000 psi	
	@Thickness 12.7 mm, Temperature 25.0 °C	@Thickness 0.500 in, Temperature 77.0 °F	as welded
	1120 MPa	162000 psi	
	@Thickness 25.4 mm, Temperature 25.0 °C	@Thickness 1.00 in, Temperature 77.0 °F	Welded then age-hardened
	1129 MPa	163700 psi	
	@Thickness 12.7 mm, Temperature 25.0 °C	@Thickness 0.500 in, Temperature 77.0 °F	Welded then age-hardened
Tensile Strength, Yield	434 MPa	62900 psi	
	@Strain 0.200 %, Thickness 25.4 mm	@Strain 0.200 %, Thickness 1.00 in	as welded
	442 MPa	64100 psi	
	@Strain 0.200 %, Thickness 12.7 mm	@Strain 0.200 %, Thickness 0.500 in	as welded
	758 MPa	110000 psi	
	@Strain 0.200 %, Thickness 12.7 mm	@Strain 0.200 %, Thickness 0.500 in	Welded then age-hardened
	763 MPa	111000 psi	
	@Strain 0.200 %, Thickness 25.4 mm	@Strain 0.200 %, Thickness 1.00 in	Welded then age-hardened
Elongation at Break	17.8 %	17.8 %	
	@Thickness 25.4 mm, Temperature 25.0 °C	@Thickness 1.00 in, Temperature 77.0 °F	Welded then age-hardened
	27.5 %	27.5 %	
	@Thickness 12.7 mm, Temperature 25.0 °C	@Thickness 0.500 in, Temperature 77.0 °F	Welded then age-hardened
	39.4 %	39.4 %	
	@Thickness 25.4 mm, Temperature 25.0 °C	@Thickness 1.00 in, Temperature 77.0 °F	as welded
	46.2 %	46.2 %	
	@Thickness 12.7 mm, Temperature 25.0 °C	@Thickness 0.500 in, Temperature 77.0 °F	as welded
Modulus of Elasticity	181 GPa	26300 ksi	
	@Temperature 600 °C	@Temperature 1110 °F	Dynamic
	195 GPa	28300 ksi	
			Dynamic

Mechanical Properties	@Temperature 500 °C Metric	@Temperature 932 °F English	Comments
	205 GPa	29700 ksi	Dynamic
	@Temperature 400 °C	@Temperature 752 °F	
	209 GPa	30300 ksi	Dynamic
	@Temperature 300 °C	@Temperature 572 °F	
	211 GPa	30600 ksi	Dynamic
	@Temperature 200 °C	@Temperature 392 °F	
	218 GPa	31600 ksi	Dynamic
	@Temperature 100 °C	@Temperature 212 °F	
	223 GPa	32300 ksi	Dynamic
	@Temperature 25.0 °C	@Temperature 77.0 °F	
Charpy Impact	46.0 J	33.9 ft-lb	Welded then age-hardened
	@Thickness 12.7 mm, Temperature -196 °C	@Thickness 0.500 in, Temperature -321 °F	
	62.0 J	45.7 ft-lb	Welded then age-hardened
	@Thickness 12.7 mm, Temperature 25.0 °C	@Thickness 0.500 in, Temperature 77.0 °F	
	157 J	116 ft-lb	as welded
	@Thickness 12.7 mm, Temperature -196 °C	@Thickness 0.500 in, Temperature -321 °F	
	197 J	145 ft-lb	as welded
	@Thickness 12.7 mm, Temperature 25.0 °C	@Thickness 0.500 in, Temperature 77.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	11.6 $\mu\text{m}/\text{m}\cdot\text{°C}$	6.44 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 25.0 - 100 °C	@Temperature 77.0 - 212 °F	
	12.0 $\mu\text{m}/\text{m}\cdot\text{°C}$	6.67 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 25.0 - 200 °C	@Temperature 77.0 - 392 °F	
	12.4 $\mu\text{m}/\text{m}\cdot\text{°C}$	6.89 $\mu\text{in}/\text{in}\cdot\text{°F}$	
	@Temperature 25.0 - 300 °C	@Temperature 77.0 - 572 °F	
	12.7 $\mu\text{m}/\text{m}\cdot\text{°C}$	7.06 $\mu\text{in}/\text{in}\cdot\text{°F}$	

Thermal Properties	Metric @Temperature 25.0 - 400 °C	English @Temperature 77.0 - 750 °F	Comments
	13.1 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	7.28 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	
	@Temperature 25.0 - 500 °C	@Temperature 77.0 - 932 °F	
	13.3 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	7.39 $\mu\text{in}/\text{in}\cdot^{\circ}\text{F}$	
	@Temperature 25.0 - 600 °C	@Temperature 77.0 - 1110 °F	
Specific Heat Capacity	0.412 J/g-°C	0.0985 BTU/lb-°F	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
	0.434 J/g-°C	0.104 BTU/lb-°F	
	@Temperature 100 °C	@Temperature 212 °F	
	0.451 J/g-°C	0.108 BTU/lb-°F	
	@Temperature 200 °C	@Temperature 392 °F	
	0.465 J/g-°C	0.111 BTU/lb-°F	
	@Temperature 300 °C	@Temperature 572 °F	
	0.477 J/g-°C	0.114 BTU/lb-°F	
	@Temperature 400 °C	@Temperature 752 °F	
	0.488 J/g-°C	0.117 BTU/lb-°F	
	@Temperature 500 °C	@Temperature 932 °F	
	0.504 J/g-°C	0.120 BTU/lb-°F	
	@Temperature 600 °C	@Temperature 1110 °F	
Thermal Conductivity	11.8 W/m-K	81.9 BTU-in/hr-ft ² -°F	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
	13.5 W/m-K	93.7 BTU-in/hr-ft ² -°F	
	@Temperature 100 °C	@Temperature 212 °F	
	15.4 W/m-K	107 BTU-in/hr-ft ² -°F	
	@Temperature 200 °C	@Temperature 392 °F	
	17.1 W/m-K	119 BTU-in/hr-ft ² -°F	
	@Temperature 300 °C	@Temperature 572 °F	
	18.6 W/m-K	129 BTU-in/hr-ft ² -°F	
	@Temperature 400 °C	@Temperature 752 °F	
	20.5 W/m-K	142 BTU-in/hr-ft ² -°F	

Thermal Properties	Metric	English	Comments
	@Temperature 500 °C	@Temperature 932 °F	
	22.4 W/m-K	155 BTU-in/hr-ft ² -°F	
	@Temperature 600 °C	@Temperature 1110 °F	
Melting Point	1304 - 1368 °C	2379 - 2494 °F	
Solidus	1304 °C	2379 °F	
Liquidus	1368 °C	2494 °F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	<= 0.50 %	<= 0.50 %	
Boron, B	<= 0.0060 %	<= 0.0060 %	
Carbon, C	<= 0.010 %	<= 0.010 %	
Chromium, Cr	21 %	21 %	
Cobalt, Co	<= 1.0 %	<= 1.0 %	
Iron, Fe	<= 2.0 %	<= 2.0 %	
Manganese, Mn	<= 0.80 %	<= 0.80 %	
Molybdenum, Mo	17 %	17 %	
Nickel, Ni	57 %	57 %	as balance
Silicon, Si	<= 0.080 %	<= 0.080 %	
Tungsten, W	<= 1.0 %	<= 1.0 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000980 ohm-cm	0.0000980 ohm-cm	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
	0.000100 ohm-cm	0.000100 ohm-cm	
	@Temperature 100 °C	@Temperature 212 °F	
	0.000104 ohm-cm	0.000104 ohm-cm	
	@Temperature 200 °C	@Temperature 392 °F	
	0.000108 ohm-cm	0.000108 ohm-cm	
	@Temperature 300 °C	@Temperature 572 °F	
	0.000112 ohm-cm	0.000112 ohm-cm	

Electrical Properties	Metric	English	Comments
	@Temperature 400 °C	@Temperature 752 °F	
	0.000115 ohm-cm	0.000115 ohm-cm	
	@Temperature 500 °C	@Temperature 932 °F	
	0.000117 ohm-cm	0.000117 ohm-cm	
	@Temperature 600 °C	@Temperature 1110 °F	

Processing Properties	Metric	English	Comments
Adapter Temperature	607.2 °C	1125 °F	Step 2, follow by air cooling
	@Time 115000 sec	@Time 32.0 hour	
	704 °C	1300 °F	Step 1; then furnace cool to step 2
	@Time 57600 sec	@Time 16.0 hour	
Annealing Temperature	1079 °C	1975 °F	Followed by rapid air cooling or water quench

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China