

Haynes Hastelloy® G-35® Nickel Alloy Synergic Gas Metal Arc Welded (GMAW) All Weld Cruciform

Category : Metal , Nonferrous Metal , Nickel Alloy

Material Notes:

Known for its corrosion performance, HASTELLOY® G-35® alloy was designed to resist "wet process" phosphoric acid, which is widely used in the production of fertilizers. Tests indicate that it is far superior to HASTELLOY® G-30® alloy and stainless steels, in this chemical. It was also designed to resist localized attack in the presence of chlorides, since under-deposit attack is a potential problem in evaporators used to concentrate "wet process" phosphoric acid. As a result of its high-chromium content, G-35 alloy is extremely resistant to other oxidizing acids, such as nitric, and mixtures containing nitric acid. It possesses moderate resistance to reducing acids, as a result of its appreciable molybdenum content, and, unlike other nickel-chromium-molybdenum alloys, it is very resistant to "caustic dealloying" in hot sodium hydroxide. Finally, G-35 alloy is much less susceptible to chloride-induced stress corrosion cracking than the high chromium stainless steels and nickel-chromium-iron alloys traditionally used in "wet process" phosphoric acid. G-35 alloy is available in the form of plate, sheet, strip, billet, bar, wire, covered electrodes, pipe, and tubing. Potential Applications: "Wet process" phosphoric acid evaporators. Pickling in nitric and hydrofluoric acids. Chemical process industry systems involving nitric and chlorides. Caustic neutralizing systems. Systems requiring resistance to high temperature corrosion at 800-1200°F. G-35 alloy is covered by ASME, ASTM, and DIN specifications. Welding: The weldability of G-35 alloy is similar to that of C-276 alloy. To weld G-35 alloy, three processes are commonly used. For sheet welds and plate root passes, gas tungsten arc (GTAW) welding is favored. For plate welds, the gas metal arc (GMAW) process is preferred. For field welding, the shielded metal arc process, using coated electrodes, is favored. Submerged arc welding is not recommended as this process is characterized by high heat input to the base metal and slow cooling of the weld. To minimize the precipitation of second phases in regions affected by the heat of welding, a maximum interpass temperature of 93°C (200°F) is recommended for G-35 alloy. Also, welding of cold-worked materials is strongly discouraged, since they sensitize more quickly and induce residual stresses. A full solution anneal, followed by water quenching, is recommended for cold-worked structures, prior to welding. Joining Base Metal Preparation: The joint surface and adjacent area should be thoroughly cleaned before welding. All grease, oil crayon marks, sulfur compounds, and other foreign matter should be removed. Filler Metal Selections: For gas tungsten arc and gas metal arc welding, G-35 filler wire is suggested. For shielded metal arc welding, G-35 covered electrodes are suggested. Heat Treatment: Wrought forms of HASTELLOY G-35 alloy are furnished in the solution annealed condition, unless otherwise specified. The standard solution annealing treatment consists of heating to 1121°C (2050°F) followed by rapid air-cooling or water quenching. Parts which have been hot formed should be solution annealed prior to final fabrication or installation. Forming: G-35 alloy has excellent forming characteristics, and cold forming is the preferred method of shaping. The alloy can be easily cold worked due to its good ductility. The alloy is generally stiffer than the austenitic stainless steels; therefore, more energy is required during cold forming. Tensile properties reported are for transverse synergic gas metal arc welded all-weld-metal specimens from Cruciform. Other properties are typical of the alloy. Data provided by the manufacturer, Haynes International, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Haynes-Hastelloy-G-35-Nickel-Alloy-Synergic-Gas-Metal-Arc-Welded-GMAW-All-Weld-Cruciform.php

Physical Properties	Metric	English	Comments
Density	8.22 g/cc	0.297 lb/in ³	

Mechanical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	@Diameter 12.7 mm, Temperature 538 °C	@Diameter 0.500 in, Temperature 1000 °F	
	538 MPa	78000 psi	
	@Diameter 12.7 mm, Temperature 260 °C	@Diameter 0.500 in, Temperature 500 °F	
	696 MPa	101000 psi	
Tensile Strength, Yield	@Diameter 12.7 mm, Temperature 25.0 °C	@Diameter 0.500 in, Temperature 77.0 °F	
	302 MPa	43800 psi	0.2% Offset
	@Diameter 12.7 mm, Temperature 538 °C	@Diameter 0.500 in, Temperature 1000 °F	
	336 MPa	48700 psi	0.2% Offset
Elongation at Break	@Diameter 12.7 mm, Temperature 260 °C	@Diameter 0.500 in, Temperature 500 °F	
	486 MPa	70500 psi	0.2% Offset
	@Diameter 12.7 mm, Temperature 25.0 °C	@Diameter 0.500 in, Temperature 77.0 °F	
	42 %	42 %	
Modulus of Elasticity	@Diameter 12.7 mm, Temperature 538 °C	@Diameter 0.500 in, Temperature 1000 °F	
	43 %	43 %	
	@Diameter 12.7 mm, Temperature 25.0 °C	@Diameter 0.500 in, Temperature 77.0 °F	
	46 %	46 %	
Dynamic	@Diameter 12.7 mm, Temperature 260 °C	@Diameter 0.500 in, Temperature 500 °F	
	170 GPa	24700 ksi	Dynamic
	@Temperature 649 °C	@Temperature 1200 °F	
	177 GPa	25700 ksi	Dynamic
Dynamic	@Temperature 538 °C	@Temperature 1000 °F	
	183 GPa	26500 ksi	Dynamic
	@Temperature 427 °C	@Temperature 801 °F	
	189 GPa	27400 ksi	Dynamic
Dynamic	@Temperature 316 °C	@Temperature 601 °F	
	204 GPa	29600 ksi	

Mechanical Properties	Metric @ Temperature 25.0 °C	English @ Temperature 77.0 °F	Dynamic Comments
-----------------------	---------------------------------	----------------------------------	---------------------

Thermal Properties	Metric	English	Comments
CTE, linear	12.3 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	6.83 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	
	@Temperature 21.0 - 100 °C	@Temperature 69.8 - 212 °F	
	12.6 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	7.00 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	
	@Temperature 21.0 - 200 °C	@Temperature 69.8 - 392 °F	
	13.2 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	7.33 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	
	@Temperature 21.0 - 300 °C	@Temperature 69.8 - 572 °F	
	13.4 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	7.44 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	
	@Temperature 21.0 - 400 °C	@Temperature 69.8 - 752 °F	
	13.6 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	7.56 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	
	@Temperature 21.0 - 500 °C	@Temperature 69.8 - 932 °F	
	14.4 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$	8.00 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$	
	@Temperature 21.0 - 600 °C	@Temperature 69.8 - 1110 °F	
Specific Heat Capacity	0.450 J/g-°C	0.108 BTU/lb-°F	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
	0.470 J/g-°C	0.112 BTU/lb-°F	
	@Temperature 100 °C	@Temperature 212 °F	
	0.490 J/g-°C	0.117 BTU/lb-°F	
	@Temperature 200 °C	@Temperature 392 °F	
	0.510 J/g-°C	0.122 BTU/lb-°F	
	@Temperature 300 °C	@Temperature 572 °F	
	0.530 J/g-°C	0.127 BTU/lb-°F	
	@Temperature 400 °C	@Temperature 752 °F	
	0.530 J/g-°C	0.127 BTU/lb-°F	
	@Temperature 500 °C	@Temperature 932 °F	
	0.600 J/g-°C	0.143 BTU/lb-°F	

Thermal Properties	@Temperature 600 °C Metric	@Temperature 1110 °F English	Comments
Thermal Conductivity	10.0 W/m-K	69.4 BTU-in/hr-ft²-°F	
	@Temperature 25.0 °C	@Temperature 77.0 °F	
	12.0 W/m-K	83.3 BTU-in/hr-ft²-°F	
	@Temperature 100 °C	@Temperature 212 °F	
	14.0 W/m-K	97.2 BTU-in/hr-ft²-°F	
	@Temperature 200 °C	@Temperature 392 °F	
	16.0 W/m-K	111 BTU-in/hr-ft²-°F	
	@Temperature 300 °C	@Temperature 572 °F	
	18.0 W/m-K	125 BTU-in/hr-ft²-°F	
	@Temperature 400 °C	@Temperature 752 °F	
	19.0 W/m-K	132 BTU-in/hr-ft²-°F	
	@Temperature 500 °C	@Temperature 932 °F	
	23.0 W/m-K	160 BTU-in/hr-ft²-°F	
	@Temperature 600 °C	@Temperature 1110 °F	
Melting Point	1332 - 1361 °C	2430 - 2482 °F	
Solidus	1332 °C	2430 °F	
Liquidus	1361 °C	2482 °F	

Component Elements Properties	Metric	English	Comments
Aluminum, Al	<= 0.40 %	<= 0.40 %	
Carbon, C	<= 0.050 %	<= 0.050 %	
Chromium, Cr	33 %	33 %	
Iron, Fe	<= 2.0 %	<= 2.0 %	
Manganese, Mn	<= 0.50 %	<= 0.50 %	
Molybdenum, Mo	8.0 %	8.0 %	
Nickel, Ni	55.5 %	55.5 %	as balance
Silicon, Si	<= 0.60 %	<= 0.60 %	

Electrical Properties	Metric	English	Comments
	0.000118 ohm-cm	0.000118 ohm-cm	

Electrical Properties	Metric	English	Comments
	@ Temperature 25.0 °C	@ Temperature 77.0 °F	
	0.000119 ohm-cm	0.000119 ohm-cm	
	@Temperature 100 °C	@Temperature 212 °F	
	0.000120 ohm-cm	0.000120 ohm-cm	
	@Temperature 200 °C	@Temperature 392 °F	
	0.000121 ohm-cm	0.000121 ohm-cm	
	@Temperature 300 °C	@Temperature 572 °F	
	0.000122 ohm-cm	0.000122 ohm-cm	
	@Temperature 400 °C	@Temperature 752 °F	
	0.000124 ohm-cm	0.000124 ohm-cm	
	@Temperature 500 °C	@Temperature 932 °F	
	0.000125 ohm-cm	0.000125 ohm-cm	
	@Temperature 600 °C	@Temperature 1110 °F	

Processing Properties	Metric	English	Comments
Annealing Temperature	1120 °C	2050 °F	Followed by rapid air cooling or water quench

Descriptive Properties	Value	Comments
Thermal Diffusivity	0.028 cm ² /s	25°C
	0.031 cm ² /s	100°C
	0.034 cm ² /s	200°C
	0.038 cm ² /s	300°C
	0.042 cm ² /s	400°C
	0.045 cm ² /s	500°C
	0.048 cm ² /s	600°C

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China