

Haynes Hastelloy® N, 1.6 mm sheet, heat treated at 1175°C, welded and tested as welded

Category : Metal , Nonferrous Metal , Nickel Alloy , Superalloy

Material Notes:

Applications include containers for molten fluoride salts. Good oxidation resistance to hot fluoride salts at 705-870°C (1300-1600°F), good oxidation resistance in air. Data provided by the manufacturer, Haynes International, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Haynes-Hastelloy-N-16-mm-sheet-heat-treated-at-1175C-welded-and-tested-as-welded.php

Physical Properties	Metric	English	Comments
Density	8.86 g/cc	0.320 lb/in ³	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	800 MPa	116000 psi	
	359 MPa	52100 psi	
	@Temperature 816 °C	@Temperature 1500 °F	
	438 MPa	63500 psi	
	@Temperature 704 °C	@Temperature 1300 °F	
	493 MPa	71500 psi	
	@Temperature 649 °C	@Temperature 1200 °F	
Elongation at Break	37.5 %	37.5 %	in 50.8 mm
	8.5 %	8.5 %	in 50.8 mm
	@Temperature 816 °C	@Temperature 1500 °F	
	10.5 %	10.5 %	in 50.8 mm
	@Temperature 704 °C	@Temperature 1300 °F	
	17 %	17 %	in 50.8 mm
	@Temperature 649 °C	@Temperature 1200 °F	
Modulus of Elasticity	122 GPa	17700 ksi	
	@Temperature 1049 °C	@Temperature 1920 °F	
	136 GPa	19700 ksi	

Mechanical Properties	Metric @Temperature 1000 Â°C	English @Temperature 1830 Â°F	Comments
	143 GPa	20700 ksi	
	@Temperature 954 Â°C	@Temperature 1750 Â°F	
	151 GPa	21900 ksi	
	@Temperature 904 Â°C	@Temperature 1660 Â°F	
	157 GPa	22800 ksi	
	@Temperature 854 Â°C	@Temperature 1570 Â°F	
	163 GPa	23600 ksi	
	@Temperature 800 Â°C	@Temperature 1470 Â°F	
	171 GPa	24800 ksi	
	@Temperature 700 Â°C	@Temperature 1290 Â°F	
	181 GPa	26300 ksi	
	@Temperature 577 Â°C	@Temperature 1070 Â°F	
	181 GPa	26300 ksi	
	@Temperature 632 Â°C	@Temperature 1170 Â°F	
	187 GPa	27100 ksi	
	@Temperature 500 Â°C	@Temperature 932 Â°F	
	192 GPa	27800 ksi	
	@Temperature 410 Â°C	@Temperature 770 Â°F	
	202 GPa	29300 ksi	
	@Temperature 221 Â°C	@Temperature 430 Â°F	
	219 GPa	31800 ksi	
	@Temperature 14.0 Â°C	@Temperature 57.2 Â°F	

Thermal Properties	Metric	English	Comments
CTE, linear	12.3 Âµm/m-Â°C	6.83 Âµin/in-Â°F	
	@Temperature 21.0 - 316 Â°C	@Temperature 69.8 - 601 Â°F	

Thermal Properties	Metric µm/m-Â°C	English µin/in-Â°F	Comments
	@Temperature 21.0 - 427 Â°C	@Temperature 69.8 - 801 Â°F	
	13.4 Âµm/m-Â°C	7.44 Âµin/in-Â°F	
	@Temperature 21.0 - 538 Â°C	@Temperature 69.8 - 1000 Â°F	
	14.0 Âµm/m-Â°C	7.78 Âµin/in-Â°F	
	@Temperature 21.0 - 649 Â°C	@Temperature 69.8 - 1200 Â°F	
	14.7 Âµm/m-Â°C	8.17 Âµin/in-Â°F	
	@Temperature 21.0 - 760 Â°C	@Temperature 69.8 - 1400 Â°F	
	15.3 Âµm/m-Â°C	8.50 Âµin/in-Â°F	
	@Temperature 21.0 - 871 Â°C	@Temperature 69.8 - 1600 Â°F	
	15.8 Âµm/m-Â°C	8.78 Âµin/in-Â°F	
	@Temperature 21.0 - 982 Â°C	@Temperature 69.8 - 1800 Â°F	
Specific Heat Capacity	0.419 J/g-Â°C	0.100 BTU/lb-Â°F	
	@Temperature 100 Â°C	@Temperature 212 Â°F	
	0.440 J/g-Â°C	0.105 BTU/lb-Â°F	
	@Temperature 200 Â°C	@Temperature 392 Â°F	
	0.456 J/g-Â°C	0.109 BTU/lb-Â°F	
	@Temperature 300 Â°C	@Temperature 572 Â°F	
	0.469 J/g-Â°C	0.112 BTU/lb-Â°F	
	@Temperature 400 Â°C	@Temperature 752 Â°F	
	0.477 J/g-Â°C	0.114 BTU/lb-Â°F	
	@Temperature 480 Â°C	@Temperature 896 Â°F	
0.485 J/g-Â°C	0.116 BTU/lb-Â°F		
@Temperature 540 Â°C	@Temperature 1000 Â°F		
0.523 J/g-Â°C	0.125 BTU/lb-Â°F		
@Temperature 570 Â°C	@Temperature 1060 Â°F		
0.565 J/g-Â°C	0.135 BTU/lb-Â°F		

Thermal Properties	Metric	English	Comments
	@Temperature 590 Â°C	@Temperature 1090 Â°F	
	0.578 J/g-Â°C	0.138 BTU/lb-Â°F	
	@Temperature 680 Â°C	@Temperature 1260 Â°F	
	0.578 J/g-Â°C	0.138 BTU/lb-Â°F	
	@Temperature 700 Â°C	@Temperature 1290 Â°F	
	0.582 J/g-Â°C	0.139 BTU/lb-Â°F	
	@Temperature 660 Â°C	@Temperature 1220 Â°F	
	0.586 J/g-Â°C	0.140 BTU/lb-Â°F	
	@Temperature 620 Â°C	@Temperature 1150 Â°F	
Thermal Conductivity	11.5 W/m-K	79.8 BTU-in/hr-ftÂ²- Â°F	RT
	13.1 W/m-K	90.9 BTU-in/hr-ftÂ²- Â°F	
	@Temperature 100 Â°C	@Temperature 212 Â°F	
	13.1 W/m-K	90.9 BTU-in/hr-ftÂ²- Â°F	
	@Temperature 200 Â°C	@Temperature 392 Â°F	
	14.4 W/m-K	99.9 BTU-in/hr-ftÂ²- Â°F	
	@Temperature 300 Â°C	@Temperature 572 Â°F	
	16.5 W/m-K	115 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 400 Â°C	@Temperature 752 Â°F	
	18.0 W/m-K	125 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 500 Â°C	@Temperature 932 Â°F	
	20.3 W/m-K	141 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 600 Â°C	@Temperature 1110 Â°F	
	23.6 W/m-K	164 BTU-in/hr-ftÂ²-Â°F	
	@Temperature 700 Â°C	@Temperature 1290 Â°F	
Melting Point	1300 - 1400 Â°C	2370 - 2550 Â°F	

Solidus	1300 Å°C	2370 Å°F	
Thermal Properties	Metric	English	Comments
Liquidus	1400 Å°C	2550 Å°F	

Component Elements Properties	Metric	English	Comments
Al + Ti	<= 0.50 %	<= 0.50 %	
Carbon, C	<= 0.080 %	<= 0.080 %	
Chromium, Cr	7.0 %	7.0 %	
Cobalt, Co	<= 0.20 %	<= 0.20 %	
Copper, Cu	<= 0.35 %	<= 0.35 %	
Iron, Fe	<= 5.0 %	<= 5.0 %	
Manganese, Mn	<= 0.80 %	<= 0.80 %	
Molybdenum, Mo	16 %	16 %	
Nickel, Ni	71 %	71 %	
Silicon, Si	<= 1.0 %	<= 1.0 %	
Tungsten, W	<= 0.50 %	<= 0.50 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.000120 ohm-cm	0.000120 ohm-cm	RT
	0.000124 ohm-cm	0.000124 ohm-cm	
	@Temperature 815 Å°C	@Temperature 1500 Å°F	
	0.000126 ohm-cm	0.000126 ohm-cm	
	@Temperature 705 Å°C	@Temperature 1300 Å°F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China