

Heatbath/Park 10699 Class IV Salt Neutral Salt

Category : Ceramic , Fluid , Quenchant

Material Notes:

Basically the same as Uni-Hard, except that it is formulated per MIL-S-10699-B, Class 4 Information provided by Heatbath Corporation - Park Metallurgical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_HeatbathPark-10699-Class-IV-Salt-Neutral-Salt.php

Thermal Properties	Metric	English	Comments
Melting Point	549 Â°C	1020 Â°F	
Maximum Service Temperature, Air	927 Â°C	1700 Â°F	Upper limit of working range
Minimum Service Temperature, Air	593 Â°C	1100 Â°F	Lower limit of working range

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China