

Heatbath/Park #50 Oil Quench

Category: Fluid, Quenchant

Material Notes:

Low viscosity quench oil that approaches water in quench speed, yet gives a more uniform, less severe quench than water. Recommended for open quench system operating below 120°C.Information provided by Heatbath Corporation - Park Metallurgical.

Order this product through the following link:

http://www.lookpolymers.com/polymer_HeatbathPark-50-Oil-Quench.php

Physical Properties	Metric	English	Comments
Saybolt Viscosity at 100°F	45 SUS	45 SUS	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	48.9 °C	120 °F	Upper limit of working range
Minimum Service Temperature, Air	10.0 °C	50.0 °F	Lower limit of working range
Flash Point	138 °C	280 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China