

## Heatbath/Park #900 High Speed Hardening Salt

Category : Ceramic , Fluid , Quenchant

### Material Notes:

For quenching and tempering steel. #900 is especially suited for oil hardening followed by relatively high draw, since no washing is required between quench and draw. #900 is less hygroscopic than #800 and can be used at higher temperatures. Formulated per MIL-S-10699-B, Class 5 Information provided by Heatbath Corporation - Park Metallurgical.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_HeatbathPark-900-High-Speed-Hardening-Salt.php](http://www.lookpolymers.com/polymer_HeatbathPark-900-High-Speed-Hardening-Salt.php)

Thermal Properties	Metric	English	Comments
Melting Point	493 Â°C	920 Â°F	
Maximum Service Temperature, Air	704 Â°C	1300 Â°F	Upper limit of working range
Minimum Service Temperature, Air	538 Â°C	1000 Â°F	Lower limit of working range

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China